



# Standard Practice for Rubber—Standard Temperatures For Testing<sup>1</sup>

This standard is issued under the fixed designation D 1349; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This practice establishes a list of standard temperatures from which selection may be made for any specific test or test method. Any standard or specification which specifies test temperatures not listed shall take precedence over this practice.

1.2 These temperatures do not apply to mixing, processing, or vulcanizing temperatures for rubber compounds. Any standard requiring preparation of a particular rubber compound should specify the conditions to be used.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Test Temperatures

2.1 The test temperatures are as follows:

°C	°F
-75	-103
-55	-67
-40	-40
-25	-13
-10	14
0	32
23	73.4
40	104
55	131
70	158
85	185
100	212
125	257
135	275
150	302
160	320
175	347
200	392
225	437
250	482

2.2 Tolerances for the test temperature, unless otherwise specified in a particular method, shall be  $\pm 2^{\circ}\text{C}$  or  $\pm 3.6^{\circ}\text{F}$ . This tolerance is the maximum allowable variation in the temperature of the space enclosing the specimens being tested. The average temperature of the space shall be as close as practicable to the specified temperature.

2.3 Unless otherwise specified, conditioning and testing of materials known to be sensitive to variations in temperature or relative humidity, shall be carried out at a temperature of  $23 \pm 2^{\circ}\text{C}$  ( $73.4 \pm 3.6^{\circ}\text{F}$ ) and a relative humidity of  $50 \pm 5\%$ .

## 3. Keywords

3.1 standard test temperatures

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D-11 on Rubber and is the direct responsibility of Subcommittee D11.14 on Time and Temperature-Dependent Physical Properties.

Current edition approved February 10, 1999. Published February 1999. Originally published as D1349 – 54 T. Last previous edition D1349 – 87 (1992)<sup>ε1</sup>.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*