

This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D 3183 – 84 (Reapproved 1998)



Designation: D 3183 – 02

Standard Practice for Rubber—Preparation of Pieces for Test Purposes from Products¹

This standard is issued under the fixed designation D 3183; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

¹ This practice is under the jurisdiction of ASTM Committee D-11 on Rubber and is the direct responsibility of Subcommittee D11.10 on Physical Testing. Current edition approved March 30, 1984; Dec. 10, 2002. Published May 1984; January 2003. Originally published as D 3183 – 73; approved in 1973. Last previous edition approved in 1984 as D 3183 – 7384.

1. Scope

1.1 This practice describes methods for the preparation of pieces of a rubber vulcanizate that is not in the form of sheet. Such pieces are used as a source from which specimens are obtained for testing.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

D 3182 Practice for Rubber—Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets²

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *piece*—a term used for a rubber vulcanizate in a size and shape suitable for cutting specimens.

4. Significance and Use

4.1 This practice is used when it is necessary to test a product from which specimens cannot be cut directly. Procedures are given for preparing pieces suitable for preparing specimens of the product.

5. Conditioning

5.1 Pieces shall be prepared for specimen cutting and testing not sooner than 16 h. after vulcanization and not later than 60 days after delivery to a purchaser: (See Note 1).

NOTE 1—For production quality control, testing within 1 to 6 h after vulcanization may be necessary to monitor plant operation.

6. Pieces

6.1 Pieces shall be obtained, if possible, from the product to be tested in accordance with the specification for the particular product. The pieces shall be prepared in accordance with Section 7.

6.2 When it is not feasible to prepare suitable pieces from the product, specially molded pieces or sheets may be prepared from the same unvulcanized rubber compound used to prepare the product. The sheets shall be vulcanized in accordance with Practice D 3182 and shall have an equivalent state of vulcanization judged from such properties as can be determined on the product. The sheets shall have one of the following thicknesses unless another thickness is technically necessary:

mm	in.
2 ± 0.2	(0.08 ± 0.008)
4 ± 0.2	(0.16 ± 0.008)

² *Annual Book of ASTM Standards*, Vol 09.01.

6.3 ± 0.3
12.5 ± 0.5

(0.25 ± 0.12)
(0.50 ± 0.02)

7. Preparation of Pieces

7.1 Rubber vulcanizates, particularly products, may not have a suitable form or size for use in cutting specimens for test. Procedures in this section describe the preparation of pieces from vulcanizates that are too thick, have uneven surfaces, or contain textiles.

7.1.1 After the piece is prepared, it shall rest at least 30 min before the specimens are cut.

7.2 *Separation of Textiles*—The separation should preferably avoid the use of a swelling liquid. If this is not possible, use commercial iso-octane. Take care to avoid excessive stretching of the rubber during the separation, by separating a little at a time while the rubber is gripped near the point of separation. If a liquid is used, place the rubber so as to permit free evaporation of the liquid. Allow time for the complete evaporation of the liquid before the specimens are cut and tested. Some skiving machines can separate plies of rubber as in belts, hose, and tires (see 7.4).

7.3 *Cutting Knife Procedure*—This procedure is based on commercial slicing machines. The machine consists of a motor- or hand-driven disk cutter of suitable diameter with a movable cutting table that transports the sample to the cutting edge. An adjustable slow-feed mechanism is fitted to the cutting table that feeds the rubber forward to the line of cut and controls the thickness of the slice. Clamping devices should be available to secure the rubber. The knife should be lubricated with a mild soap solution to ease the cutting operation.

7.4 *Skiving Procedure*—This procedure is based on commercial leather slitting machinery, and convenient types are available for cutting about 50-mm (2-in.) wide strips with thicknesses up to about 12 mm (0.5 in.). Adjustments should be available to vary the thickness of cut, and feed rollers should be provided to transport the material past the knife. Provision should be made for continuous sharpening of the cutting edge. Attachments are available for splitting and cutting sections from cable sheathing and hose.

7.5 *Buffing Techniques*—Use the buffing techniques described below when it is necessary to remove any unevenness of surface. Unevenness of surface may result from contact with fabric components, cutting techniques, or other reasons.

7.5.1 *Abrasive Wheels*—The buffing apparatus, commonly known as an **Emerson Type Rubber Buffer**,³ should consist of a grinder with motor-driven abrasive wheel. It is important that the wheel should run true, without vibration, and that the abrasive surface based on aluminum oxide or silicon carbide is true and sharp. The grinder should be equipped with a slow-feed mechanism so that very light cuts may be made to avoid over-heating of the rubber. Suitable means should be provided for securing the rubber to prevent excessive deformation and for controlled traversing of the rubber pass the abrasive wheel (Note 2). In operation the depth of cut should not exceed approximately 0.2 mm (0.008 in.). The successive cuts should be progressively thinner to avoid over-heating. Do not carry out buffing beyond the point where unevenness of thickness has been eliminated. For removal of greater thicknesses of rubber, use the cutting techniques indicated in 7.3 and 7.4.

NOTE 2—Wheels of 125 to 150-mm (5 to 6-in.) diameter operating at a surface speed in the range of 20 ± 5 m/s (4000 ± 700 ft/min) of grit size 0.42 to 1.00 mm (grit No. 30) for roughing and of grit size 0.18 to 0.42 mm (grit No. 60) for finishing have been found suitable.

7.5.2 *Abrasive Flexible Bands*, The apparatus shall consist of either a motor-driven drum, on which a spiral helix of the abrasive is secured, or two pulleys, one motor-driven and the other adjustable to tension to centralize the movement of the band. The abrasive bands should be of textile or paper, or a combination of the two, with the abradant based on aluminum oxide or silicon carbide bonded to its surface with a resin unaffected by water. Equipment should be provided for slow feeding of the material to the abrasive band and for securing the material without excessive deformation (Note 3). In operation, cuts removing several tenths of a millimetre of rubber are practicable as the heat build up is much lower than with the method of 7.5.1. The buffing may be either against the drum, against one of the pulleys, or against the taut band between the pulleys.

NOTE 3—Grit sizes of 0.42 to 1.00 mm (grit No. 30) for roughing and of 0.05 to 0.18 mm (grit No. 100 or 180) for finishing with surface speed of the band in the range 20 ± 5 m/s (4000 ± 700 ft/min.) have been found suitable.

8. Keywords

8.1 cutting; Emerson Type rubber buffer; rubber buffer; rubber buffing; test piece; test piece preparation; test specimen; testing of finished products; skiving

³ Available from CCSi, Inc., 1145 Highbrook Ave., Suite 500, Akron, OH 44301.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).