



Designation: D 5377 – 93 (Reapproved 1998)

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Classification for Rubber Compounding Materials—Ground Coal¹

This standard is issued under the fixed designation D 5377; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification covers the compounding material known as ground coal. It is generally used in rubber compounds as a filler.

1.2 There are three grades of ground coal based on particle size, ash, and moisture. The selected values for these properties are suitable for use in a rubber compound.

2. Referenced Documents

2.1 ASTM Standards:

C 1070 Test Method for Determining Particle Size Distribution of Alumina or Quartz by Laser Light Scattering²

D 1208 Test Methods for Common Properties of Certain Pigments³

D 3174 Test Method for Ash in the Analysis Sample of Coal and Coke from Coal⁴

D 3175 Test Method for Volatile Matter in the Analysis Sample of Coal and Coke⁴

¹ This classification is under the jurisdiction of ASTM Committee D-11 on Rubber and is the direct responsibility of Subcommittee D11.20 on Compounding Materials and Procedures.

Current edition approved March 15, 1993. Published May 1993.

² *Annual Book of ASTM Standards*, Vol 15.02.

³ *Annual Book of ASTM Standards*, Vol 06.03.

⁴ *Annual Book of ASTM Standards*, Vol 05.05.

D 4371 Test Method for Determining the Washability Characteristics of Coal⁴

3. Significance and Use

3.1 Ground coal is commonly used as an inexpensive filler in rubber compounds as a direct or partial replacement for carbon black or as a diluent in the compound.

3.2 Ground coal is very compatible with most rubbers and is very easily mixed into the compound.

4. Basis of Classification

4.1 Particle size will have a direct effect on the modulus, tensile strength, and tear strength of the finished rubber.

4.2 Ash in the coal will effect the specific gravity and high ash can influence the curing characteristics of the rubber.

4.3 Moisture in the ground coal at levels of 0.5 % and above can cause blisters and scorch.

4.4 Lowering the density (specific gravity) will reduce compounding cost and affect volume loading.

4.5 Ground coal for use in rubber compounds shall conform to the three grades listed in Table 1.

5. Keywords

5.1 filler; ground coal



TABLE 1 Properties of Ground Coal

Property (Maximum Values)	Grade I	Grade II	Grade III	Test Method
Average particle size (µm) not weighted	5	6	7	C 1070
Top particle size (µm)	20	24	28	C 1070
Retained on 325 mesh (g)	0.0100	0.0450	0.0950	A
Retained on 100 mesh (g)	0.0003	0.0005	0.0010	A
Ash, %	5	6	7	D 3174
Alpha quartz, %	1.0	1.50	2.0	X-Ray Diffraction
Heat loss, % (moisture)	0.5	0.75	1.0	D 3174
Acidity	0.02	0.02	0.02	D 1208
Volatile matter, %	20	20	20	D 3175
Density (Mg/m ³) (specific gravity)	1.35	1.45	1.55	D 4371

^AMethod is being letter balloted in Subcommittee D11.11. Values based on 100 g samples.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.