



Standard Test Method for Silica—pH Value¹

This standard is issued under the fixed designation D 6739; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is used to measure the pH of a 5 % silica/water suspension or mechanical dispersion and is indicative of the relative acidity or alkalinity of the silica.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

E 70 Test Method for pH of Aqueous Solutions with the Glass Electrode²

3. Significance and Use

3.1 The pH level of silica, as measured by this test method, is known to affect the vulcanization of some rubber compounds. Refer to Test Method E 70 for a fuller understanding of pH and a more detailed procedure for making pH measurements.

4. Apparatus

4.1 *pH Meter*, (digital is recommended), having an accuracy of ± 0.05 pH and equipped with a combination electrode.

4.2 *Mortar and Pestle*.

4.3 *Beaker*, glass, 150 cm³ with watch glass.

4.4 *Magnetic Stirring Bar and Stirrer*.

5. Reagents

5.1 *Degassed, Neutral Water*. Boil a container of either distilled or deionized water for 10 min, cover, and allow to cool to room temperature, or purge the water with nitrogen gas for 20 min using a fritted bubbler.

5.2 *Buffer Solutions*, pH of 4.00, 7.00, and 10.00.

6. Procedure

6.1 Pulverize pelleted or granulated silica to a fine powder, using a mortar and pestle.

6.2 Weigh 5 g of silica to the nearest 0.1 g into a 150 cm³ glass beaker.

6.3 Add 100 cm³ of degassed, neutral water.

6.4 Cover the glass beaker with a watch glass and stir the mixture for 5 min at room temperature.

6.5 Standardize the pH meter with two buffer solutions that bracket the expected pH value of the silica. Rinse the electrode with distilled water and wipe clean after each test.

6.6 Place the electrode in the silica/water mixture, continuing to stir with the magnetic stirrer. When a constant pH is obtained, record the pH to the nearest 0.05 pH unit.

6.7 Rinse the electrode with distilled water. Store electrode in accordance with manufacturer's instructions when not in use.

7. Report

7.1 Report the following information:

7.1.1 Identification of the sample, and

7.1.2 Result obtained, reported to the nearest 0.1 unit.

8. Precision and Bias

8.1 No precision and bias study has been performed for this method.

9. Keywords

9.1 pH; silica

¹ This test method is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.20 on Compounding Materials and Procedures.

Current edition approved Nov. 10, 2001. Published January 2002.

² *Annual Book of ASTM Standards*, Vol 15.05.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).