



Standard Test Method for Approximate Acidity in Electrical Insulating Liquids by Color-Indicator Titration¹

This standard is issued under the fixed designation D 1534; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial changes were made in April 2002.

1. Scope

1.1 This test method describes the determination of the approximate total acid value of used electrical insulating liquids having viscosities less than 24 cSt at 40°C. It is a simple procedure that can be applied in the field. Where a quantitative neutralization value is required, use Test Method D 664 or Test Method D 974. These test methods should be applied in the laboratory.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 664 Test Method for Acid Number of Petroleum Products by Potentiometric Titration²

D 974 Test Method for Acid and Base Number by Color-Indicator Titration²

D 1193 Specification for Reagent Water³

3. Summary of Test Method

3.1 To determine whether the acidity is greater or less than a specified arbitrary value, a fixed volume of liquid to be tested is added to a graduated cylinder, together with a small amount of indicator (phenolphthalein) and the appropriate quantity of standard potassium hydroxide solution. The mixture is shaken and allowed to separate. The color of the aqueous layer at the bottom of the container when testing mineral oils, or at the top when testing askarels, determines whether the acidity is less than or greater than the arbitrary value chosen.

3.2 To determine the approximate total acidity, the procedure is the same as described in 3.1 except that the potassium

hydroxide solution is added in small increments until the color of the aqueous layer, after shaking and settling, is a faint pink. The volume of standard potassium hydroxide solution used determines the approximate total acid value.

4. Significance and Use

4.1 The approximate acidity of used electrical insulating oils is an estimate of the total acid value of the oil. As acid values increase, oil quality decreases. This is usually due to oxidation of the oil while in service. In general, acidic by-products produce increased dielectric loss, increased corrosivity, and may cause thermal difficulties attributable to insoluble components called “sludge.” This test method is adapted to a specific volume of oil; total acid values of 0.05 to 0.5 mg of potassium hydroxide per gram of oil is a range which is functionally significant.

5. Apparatus

5.1 *Graduated Cylinder*, 50 mL, stoppered.

5.2 *Medicine Dropper*, calibrated at 1-mL intervals.

5.3 *Calibrated Pipet*, 1-mL capacity, calibrated to deliver 0.05-mL increments.

6. Reagents and Materials

6.1 *Purity of Reagents*—Use reagent grade chemicals in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water (see Note 1) conforming to Specification D 1193.

¹ This test method is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.06 on Chemical Test.

Current edition approved Sept. 10, 1995. Published November 1995. Originally published as D 1534 – 58 T. Last previous edition D 1534– 90.

² *Annual Book of ASTM Standards*, Vol 05.01.

³ *Annual Book of ASTM Standards*, Vol 11.01.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

NOTE 1—Any grades of water listed in Specification D 1193 are deemed satisfactory for the purpose of this test method.

6.3 *Ethyl or Isopropyl Alcohol*, reagent grade.

6.4 *Phenolphthalein Indicator Solution* (100 g/L)—Dissolve 10 g of phenolphthalein in 100 mL of denatured alcohol by slight warming.

6.5 *Potassium Hydroxide, Standard Solution* (0.031 ± 0.003 N)—Prepare a 0.031 ± 0.003 N solution of potassium hydroxide (KOH) by dissolving solid KOH in a solution of equal volumes of alcohol and water in accordance with the method of preparation and standardization described in Test Method D 974 or Test Method D 664, except for the solvent and the normality.

NOTE 2—As applied to mineral oil, this normality is chosen to simplify the calculation. The 20-mL sample weighs 17.6 g, assuming an average specific gravity of 0.88. With a 17.6-g sample, 10 mL of 0.031 N KOH solution corresponds to an acid value of 1. The normality should be checked from time to time in a laboratory. If it is outside the ±0.003 tolerance, due either to evaporation of solvent or precipitation of potassium carbonate (K₂CO₃) formed by reaction with carbon dioxide (CO₂) from the atmosphere, it should be discarded.

The specific gravity of commonly used askarels is 1.56, or approximately 1.8 times that of mineral oil, and this difference must be recognized in the calculation or equipment calibration, or both, as applied to askarels.

7. Procedure

7.1 Rinse the graduated cylinder first with denatured alcohol and then with a small amount of the liquid to be tested. Pour in the test specimen to the 20-mL mark and add two drops of indicator solution with a medicine dropper. Proceed in accordance with 7.2 or 7.3.

7.2 To determine whether the acidity is greater or less than a value specified by the user, add the appropriate volume of KOH solution by dispensing from a calibrated pipet (for example, 0.5 mL if the fixed figure is 0.05 mg KOH per gram of oil, as applied to oil). Shake vigorously for several seconds, allow to settle, and observe the aqueous layer. If it is free of pink, the acidity is greater than the specified value.

7.3 To determine the approximate total acidity, add KOH solution in increments of 0.5 mL until the color of the aqueous layer, after shaking and settling, is a pale pink.

8. Calculation

8.1 For mineral oil, calculate the approximate total acid value, T , as follows:

$$T = (B - A)/10 \quad (1)$$

where:

A = test specimen used, (20) mL,
 B = liquid in the cylinder at the conclusion of the test, mL, and
 $B - A$ = KOH solution added, mL.

8.2 For askarel, calculate the approximate total acid value, T , as follows:

$$T = (B - A)/18 \quad (2)$$

NOTE 3—Other concentrations of base may be used in the titration. A less concentrated solution of KOH provides a greater volume of the aqueous layer. The calculations must then be modified to account for the difference in the concentration of base.

NOTE 4—As an alternative, prepackaged field kits have been used.⁵

9. Report

9.1 Report the following information:

9.1.1 The approximate total acidity value, T , in mgKOH/g test specimen.

9.1.2 When possible, report the acidity as “greater than” or “less than” the value specified by the user.

10. Precision and Bias

10.1 This test method provides for an approximation of total acidity, with a minimum detection level of 0.005 mgKOH/g test specimen. The total acidity is based on whether the acidity is greater or less than a user-specified value corresponding to the addition of specific volumes of KOH solution. Because this test method is only an approximation of total acidity, precision and bias statements will not be developed.

10.2 To determine quantitative acidity values, use Test Method D 664 or Test Method D 974.

11. Keywords

11.1 acidity; color titration; insulating liquid; neutralization number

⁵ Field kits, available from Gerin Co., 1109 Seventh Ave., Neptune, NJ 07753 have been found satisfactory for this purpose.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).