



# Standard Test Method for Coefficient of Thermal Expansion of Electrical Insulating Liquids of Petroleum Origin, and Askarels<sup>1</sup>

This standard is issued under the fixed designation D 1903; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the coefficient of thermal expansion of electrical insulating liquids of petroleum origin, and askarels, when used as an insulating or cooling medium, or both, in cables, transformers, oil circuit breakers, capacitors, or similar apparatus.

1.2 The values given in acceptable metric units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

D 941 Test Method for Density and Relative Density (Specific Gravity) of Liquids by Lipkin Bicapillary Pycnometer<sup>2</sup>

D 1250 Guide for Petroleum Measurement Tables<sup>2,3</sup>

D 1298 Practice for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method<sup>2</sup>

D 1810 Test Method for Specific Gravity of Askarels<sup>4</sup>

## 3. Terminology

### 3.1 Definition of Term Specific to This Standard:

3.1.1 *coefficient of thermal expansion of a liquid,  $n$* —the change in volume per unit volume per degree change in temperature. It is commonly stated as the average coefficient over a given temperature range.

## 4. Significance and Use

4.1 Knowledge of the coefficient of thermal expansion of a liquid is essential to compute the required size of a container to

accommodate a volume of liquid over the full temperature range to which it will be subjected. It is also used to compute the volume of void space that would exist in an inelastic device filled with the liquid after the liquid has cooled to a lower temperature.

## 5. Procedure for Liquids of Petroleum Origin

5.1 The coefficient of thermal expansion used in Guide D 1250, is 0.00040/°F for the temperature range from – 17.7 to 65.5°C (0 to 150°F), and petroleum oils ranging from 15.0 to 34.9° API gravity or 0.9659 to 0.8504 specific gravity. In the preparation of these tables for specific gravity values above 0.600, it has been assumed for purposes of standardization that all crude petroleum and petroleum products have uniform coefficients of expansion in the same temperature ranges. When the required accuracy of results falls within these assumptions, this value for coefficient of expansion may be used.

5.2 If closer approximation than that indicated in 5.1 is required, the coefficient of thermal expansion may be calculated by determining observed specific gravities. Determine the specific gravities at any two temperatures below 90°C (194°F) and not less than 5°C (9°F) nor more than 14°C (25°F) degrees apart by Practice D 1298. The difference in the observed specific gravities at the two temperatures divided by the product of the specific gravity at the lower temperature and the difference in the two temperatures may be used as the average coefficient of expansion for the observed temperature range.

## 6. Procedure for Askarels

6.1 Determine the specific gravity of the askarel at any two convenient temperatures below 90°C (194°F) and not less than 14°C (25°F) apart by Test Method D 1810. The difference in the observed specific gravities at the two temperatures divided by the product of the specific gravity at the lower temperature and the difference in the two temperatures may be used as the average coefficient of expansion for the observed temperature range.

6.2 If suitably calibrated hydrometers for determining the specific gravity of an askarel are not available, Test Method D 941 may be used.

## 7. Calculation

7.1 Calculate the coefficient of thermal expansion as follows:

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.07 on Physical Tests.

Current edition approved Oct. 10, 1996. Published December 1996. Originally published as D 1903 – 61. Last previous edition D 1903 – 92.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 05.01.

<sup>3</sup> These tables are issued as a separate publication in 3 volumes, American edition, British edition and Metric edition, available from the American Society for Testing and Materials, 1916 Race St., Philadelphia, PA 19103.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 10.03.

 **D 1903**

Coefficient of thermal expansion =  $(S - S_1)/(T_1 - T)$

where:

- $S$  = specific gravity at lower temperature  $T$ ,
- $S_1$  = specific gravity at higher temperature  $T_1$ ,
- $T$  = lower temperature, and
- $T_1$  = higher temperature.

**8. Precision and Bias**

8.1 This test method does not lend itself to a precision and

bias statement, due to the fact that the coefficient of thermal expansion as determined by this test method is a calculated quantity obtained from measurements made using other standard methods.

**9. Keywords**

9.1 askarels; density; electrical insulating liquids; petroleum; specific gravity; volume

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*