



Standard Test Method for 2,6-Ditertiary-Butyl Para Cresol and 2,6-Ditertiary-Butyl Phenol in Electrical Insulating Oil by Infrared Absorption ¹

This standard is issued under the fixed designation D 2668; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the weight percent of 2,6-ditertiary-butyl paracresol and 2,6-ditertiary-butyl phenol in new or used electrical insulating oil in concentrations up to 0.5 % by measuring its absorbance at the specified wavelengths in the infrared spectrum.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 923 Test Method for Sampling Electrical Insulating Liquids ²

D 2144 Test Methods for Examination of Electrical Insulating Oils by Infrared Absorption ²

D 3487 Specification for Mineral-Insulating Oil Used in Electrical Apparatus ²

3. Significance and Use

3.1 The quantitative determination of 2,6-ditertiary-butyl paracresol and 2,6-ditertiary-butyl phenol in a new electrical insulating oil measures the amount of this material that has been added to the oil as protection against oxidation. In a used oil it measures the amount remaining after oxidation products have reduced its concentration. The test is also suitable for manufacturing control and specification acceptance.

3.2 When an infrared spectrum is obtained of an electrical insulating oil inhibited with either of these compounds there is an increase in absorbance of the spectrum at several wavelengths (or wavenumbers). 2,6 ditertiary-butyl paracresol produces pronounced increases in absorbance at 2.72 μm (3680 cm^{-1}), and 11.63 μm (860 cm^{-1}). 2,6 ditertiary-butyl phenol produces pronounced increases in absorbance at 2.72 μm (3680 cm^{-1}) and 13.33 μm (750 cm^{-1}).

3.3 When making this test on other than a highly oxidized

oil or when using a double-beam spectrophotometer, it has been found convenient to obtain the spectrum between 2.5 μm (4000 cm^{-1}) and 2.9 μm (3450 cm^{-1}) because the instrument is compensated for the presence of moisture and the band is not influenced by intermolecular forces (associations). However, when testing a highly oxidized oil or when using a single-beam instrument better results may be obtained if the scan is made between 10.90 μm (918 cm^{-1}) and 14.00 μm (714 cm^{-1}).

3.4 Increased absorption at 11.63 μm (860 cm^{-1}) or 13.33 μm (750 cm^{-1}) or both, will identify the inhibitor as 2,6-ditertiary-butyl paracresol or 2,6-ditertiary-butyl phenol respectively (Note 1).

NOTE 1—The absorbance at 750 cm^{-1} for 2,6-ditertiary-butyl phenol and at 860 cm^{-1} for 2,6-ditertiary-butyl paracresol for equal concentrations will be in the approximate ratio of 2.6 to 1.

4. Apparatus

4.1 With equipment description referring to compliance, the equipment shall be in accordance with Section 6 of Test Methods D 2144.

5. Sampling

5.1 Obtain the sample in accordance with Test Method D 923.

6. Calibration and Standardization

6.1 When the manufacturer of the oil is known and the base oil is available, use it to prepare the standards. For oils of unknown origin use base oils which meet the requirements of Specification D 3487. Some base oils may provide a better match than others and therefore it is desirable to have several available.

6.2 Prepare standards containing between 0.05 and 0.4 weight percent of 2,6-ditertiary-butyl paracresol or 2,6-ditertiary-butyl phenol dissolved in an uninhibited base oil. Obtain a spectrum, at the desired band, of each standard in accordance with Test Methods D 2144. Cells with a standard path length of 0.3 to 1.0 mm are recommended. Other path lengths may be found more suitable for different instruments or particular wave lengths. Other sample path lengths may be used provided the instrument sensitivity can be adjusted to compensate for this change. The dip in the curve for the inhibited oil should provide a distinctive increase in the absorbance at the critical wavelength or frequency (Note 2). Repeat the procedure on each of the standards making three

¹ This test method is under the jurisdiction of ASTM Committee D-27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.03 on Analytical Tests.

Current edition approved Dec. 10, 1996. Published February 1997. Originally published as D 2668 – 67. Last previous edition D 2668 – 92.

² *Annual Book of ASTM Standards*, Vol 10.03.

scans on each standard. Record all settings of the spectrophotometer used in obtaining the respective spectra (Note 3).

NOTE 2—Where desired, a chart having a non-linear wavelength scale as the abscissa may be used.

NOTE 3—In making these tests, transmission-scaled charts may be used, but in this case special rulers and nomographs or logarithmic tables will be necessary for determining the intensity measurements.

6.3 The quantitative determination is made from the following equation which is derived from Beer's law:

$$\text{Absorbance} = A - A_o$$

where:

A_o = absorbance units of base oil, and

A = absorbance units of oil containing 2,6-ditertiary-butyl paracresol or 2,6-ditertiary-butyl phenol.

6.4 Designate the point of maximum absorbance of the absorbance band as Point A. Draw a tangent to the spectrum curve and a second line through Point A perpendicular to the absorbance lines, as shown in Fig. 1. Designate the intersection

of these two lines as Point A_o . Read the values of absorbance at these points on the charts of the three scans made on each test specimen to the nearest 0.001 absorbance unit (with the aid of a reading glass) and subtract the values of A_o from those of A . When the average of the three values for each of the specially prepared test specimens is plotted against the concentration, a straight line is obtained. The best straight line through the calibration data points should be drawn or determined by linear regression analysis. This is the calibration curve from which the unknown concentration of the 2,6-ditertiary-butyl paracresol or 2,6-ditertiary-butyl phenol in a test specimen may be determined. One such calibration curve is shown as Fig. 2. Fig. 3 and Fig. 4 illustrate sections of differential scans.

6.5 When frequent determinations are made on a routine basis, periodic checks of one or more standards are recommended, since the characteristics of electronics components in spectrophotometers change with time. If the absorbance of the standards differ from the calibration curve by more than the limits given in 8.2, a new curve should be




FIG. 1 Spectrum of an Electrical Insulating Oil Inhibited with 2,6-Ditertiary-Butyl Paracresol Showing Location Points A_o and A




FIG. 2 Calibration Curve for Determining the Percent by Weight of 2,6-Ditertiary-Butyl Paracresol in Electrical Insulating Oil




FIG. 3 Section of Differential Scan-A

obtained. Some laboratories have developed tighter limits than these. A new curve should also be obtained whenever there is a change in operating conditions, such as a change in light source, scan speed, etc.

NOTE 4—It is recommended that the solutions of known concentration be stored in amber-colored bottles for a period not to exceed one year in order to facilitate a quick check of the characteristics of the spectrophotometer in relation to the calibration curve.

7. Procedure

7.1 Using the quantitative scan mode, make three scans of the test specimen on which the determination of the 2,6-ditertiary-butyl paracresol or 2,6-ditertiary-butyl phenol content is to be made, at the desired band. Do this in accordance with Test Methods D 2144, except that cells having path lengths as specified in 6.2 are preferred. Use the same cell

that was used in obtaining the spectra for the calibration curve. For the Differential Method, fill the reference cell with an appropriate base oil free of oxidation inhibitors. Use a spectrophotometer which meets the requirements specified in Section 6 of Test Methods D 2144 and instrumental conditions identical to those used in obtaining the spectra for the calibration curve.

7.2 For routine tests a single scan of the test specimen is adequate as long as the instrument is capable of meeting the criteria of 8.2 using single scans to replace average values. For referee purposes, use the average of three scans of the test specimen.

7.3 Read the values of absorbance at points A_0 and A on each of the three spectra to the nearest 0.001 absorbance unit, obtain the differences and average them. Using this average

ASTM D 2668




FIG. 4 Section of Differential Scan-B

value, determine the concentration from the calibration curve.

8. Precision and Bias

8.1 *Checking Limits of Range ($A - A_o$)*—Determine the highest and lowest values of $A - A_o$ resulting from the three scans and subtract one from the other. If the resulting quantity exceeds 0.010, reject the results as excessively variable and repeat the test.

8.2 *Repeatability*—The difference between two determinations for DBPC and DBP, each obtained from the average of three scans, obtained by the same operator with the same apparatus under constant operating conditions on identical test material would, in the long run, in the normal and correct operation of the test method, exceed the value of 0.04 % by only one case in twenty.

8.3 *Reproducibility*—The difference between two

determinations for DBPC and DBP, each obtained from the average of three scans, obtained by different operators in different laboratories on identical test material would, in the long run, in the normal and correct operation of the test method, exceed the value of 0.04 % by only one case in twenty.

8.4 No statement is made about bias of this test method for measuring ditertiary-butyl paracresol or ditertiary-butyl phenol as it has not been determined.

9. Keywords

9.1 2,6-ditertiary-butyl paracresol; 2,6-ditertiary-butyl phenol; electrical insulating oil; infrared absorption; paracresol

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.