



Standard Test Method for Determination of Acid-Insoluble Residue in Biomass¹

This standard is issued under the fixed designation E 1721; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Biomass is composed largely of the following: cellulose, a polymer of glucose; hemicellulose, a complex polymer, the main chain of which consists of xylans or glucomannans; and lignin, a complex phenolic polymer. The lignin is mostly insoluble in mineral acids, unlike the other cell wall components of biomass. For this reason, lignin can be analyzed gravimetrically after hydrolyzing the cellulose and hemicellulose fractions with sulfuric acid.

1. Scope

1.1 This test method covers determination of the acid-insoluble residue of hard and soft woods, herbaceous materials (such as switchgrass and sericea), agricultural residues (such as corn stover, wheat straw, and bagasse), wastepaper (such as office waste, boxboard, and newsprint), acid and alkaline pretreated biomass, and the solid fraction of fermentation residues. All results are reported relative to the 105°C oven-dried weight of the sample.

1.2 The residue collected contains the acid-insoluble lignin and any condensed proteins from the original sample. An independent nitrogen analysis would be required to determine the acid-insoluble lignin content separate from the condensed protein fraction and is outside the scope of this test method.

1.3 The values stated in SI units are to be regarded as the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazards statements are given in Section 8 and Note 2 and Note 4.

2. Referenced Documents

2.1 ASTM Standards:

E 1690 Test Method for Determination of Ethanol Extractives in Biomass²

E 1756 Test Method for Determination of Total Solids in Biomass²

E 1757 Practice for Preparation of Biomass for Compositional Analysis²

¹ This test method is under the jurisdiction of ASTM Committee E-48 on Biotechnology and is the direct responsibility of Subcommittee E48.05 on Biomass Conversion.

Current edition approved Sept. 10, 1995. Published November 1995.

² *Annual Book of ASTM Standards*, Vol 11.05.

3. Terminology

3.1 Definitions:

3.1.1 *acid-insoluble residue*—the solid residue, corrected for acid-insoluble ash, retained on a medium-porosity filter crucible after the primary 72 % and secondary 4 % H₂SO₄ hydrolysis described in this test method. This material is primarily acid-insoluble lignin and any condensed proteins.

3.1.2 *prepared biomass*—material that has been treated in accordance with Practice E 1757 in order to raise the total solids content above 85 %, based on an oven-dried solids weight.

4. Significance and Use

4.1 The acid-insoluble residue content is used in conjunction with other assays to determine the total composition of biomass samples.

5. Interferences

5.1 The results of acid-insoluble residue analysis are affected by the incomplete hydrolysis of biomass. The results will be biased high unless the sample is hydrolyzed completely. Take care to mix the acid/biomass slurry thoroughly during the concentrated acid hydrolysis.

5.2 The results of acid-insoluble residue analysis are affected by the timing of the acid digestion steps. The insoluble residue will dissolve slowly into solution in an irreproducible fashion. The timing within this test method must be followed closely.

6. Apparatus

6.1 *Analytical Balance*, readable to 0.1 mg.

6.2 *Convection Oven*, with a temperature control of 105 ± 3°C.

6.3 *Muffle Furnace*—An electric furnace is recommended for igniting the sample. The furnace should be fitted with an indicating pyrometer or thermocouple so that the required

temperature of $575 \pm 25^\circ\text{C}$ can be maintained.

6.4 *Autoclave*, capable of maintaining $121 \pm 3^\circ\text{C}$.

6.5 *Water Bath*, set at $30 \pm 1^\circ\text{C}$.

6.6 *Desiccator*, using anhydrous calcium sulfate.

7. Reagents and Materials

7.1 *Chemicals*:

7.1.1 72 % H_2SO_4 , specific gravity 1.6389 ± 0.0012 at $15.6^\circ\text{C}/15.6^\circ\text{C}$ or 12.00 ± 0.02 M.

7.1.2 *Water*, 18 M Ω deionized.

7.2 *Materials*:

7.2.1 *Glass Serum Bottles*, 125 mL, crimp top style, with rubber stoppers and aluminum seals to fit.

7.2.2 *Glass Filtering Crucible*, 50 mL, medium porosity, with a nominal maximum pore size of 10 μm .

7.2.3 *Vacuum Adapter for Crucibles*.

8. Hazards

8.1 Handle the sulfuric acid carefully.

8.2 Use caution when handling glass bottles after the autoclave step since they may become pressurized.

9. Sampling, Test Specimens, and Test Units

9.1 Test specimens suitable for analysis with this procedure are as follows:

9.1.1 Prepared biomass samples that have been treated in accordance with Practice E 1757.

9.1.2 Extractives-free material prepared in accordance with Test Method E 1690.

9.2 The test specimen shall consist of approximately 0.3 g of sample obtained in such a manner to ensure that it is representative of the entire lot of material being tested. Prepared biomass is used in this test, but the weight of the material must be corrected to 105°C dry weight by using the percent total solids value determined in accordance with Test Method E 1756, prior to calculating the acid-insoluble residue.

9.3 The samples for total solids determination should be weighed out at the same time as those for acid-insoluble residue determination. If this is performed later, it can introduce an error in the calculation because ground biomass can gain or lose moisture rapidly when exposed to the atmosphere.

10. Procedure

10.1 Label the crucibles needed for analysis individually, and ignite them at $575 \pm 25^\circ\text{C}$ to achieve a constant weight of ± 0.3 mg. Store the ignited crucibles in a desiccator until needed.

NOTE 1—In order to determine the absolute amounts of acid-insoluble residue and acid-insoluble ash, for quality control purposes, it is useful to weigh and record the ignited crucible to the nearest 0.1 mg.

10.2 Weigh a 0.3 ± 0.01 -g sample to the nearest 0.1 mg, and place it in a test tube. Record the initial weight as W_1 .

NOTE 2—**Warning:** 72 % sulfuric acid is very corrosive and should be handled only by trained personnel.

10.3 Add 3.00 ± 0.01 mL (4.92 ± 0.01 g) of 72 % H_2SO_4 , and stir for 1 min or until mixed thoroughly.

10.4 Place the test tube in the water bath controlled to $30 \pm 1^\circ\text{C}$, and hydrolyze for 2 h.

NOTE 3—The hydrolysis time may be reduced to 1 h if the dried sample has been milled and sieved to pass through a 20-mesh sieve and be retained on a 80-mesh sieve.

10.5 Stir the sample every 15 min to ensure complete mixing and wetting.

10.6 Transfer the hydrolyzate to a glass bottle, and dilute to a 4 % acid concentration by adding 84.00 ± 0.04 mL water or by bringing the combined weight of sample, acid, and water up to 89.22 ± 0.04 g. Be careful to transfer all of the residual solids along with the hydrolysis liquor.

10.7 Stopper each of the bottles, and crimp the aluminum seals into place.

10.8 Set the autoclave to a liquid vent cycle to prevent loss of sample from the bottle in the event of a loose crimp seal. Autoclave the samples in their sealed bottles for 1 h at $121 \pm 3^\circ\text{C}$.

NOTE 4—**Warning:** Handle sealed bottles with caution after the autoclave step since they may become pressurized.

10.9 After completion of the autoclave cycle, allow the samples to cool for approximately 20 min at room temperature before removing the seals and stoppers.

10.10 Vacuum filter the hydrolysis solution through a previously ignited filtering crucible.

10.11 If a carbohydrate analysis or acid-soluble lignin analysis, or both, is desired, decant 15 to 25 mL of filtrate into a resealable container. If the aliquot is not used immediately for further analysis, store it in a refrigerator at 4°C .

NOTE 5—Acid-soluble lignin should be analyzed within 24 h and preferably within 6 h of hydrolysis.

10.12 Use hot water to wash any particles clinging to the glass bottle into the crucible and to wash the filtered residue free of acid using vacuum filtration.

10.13 Dry the crucible and its contents at $105 \pm 3^\circ\text{C}$ for 2 h or until a constant weight is achieved of ± 0.3 mg upon reheating.

10.14 Cool in the desiccator and record the weight, W_2 , of the crucible, acid insoluble residue, and acid-insoluble ash to the nearest 0.1 mg.

10.15 Place the crucible and its contents in the muffle furnace, and ignite at $575 \pm 25^\circ\text{C}$ for a minimum of 3 h, or until all the carbon is eliminated. Heat at a rate of $10^\circ\text{C}/\text{min}$ to prevent flaming. The container should be partially covered during this step if the sample tends to flare up. Avoid heating above the maximum stated temperature. Protect the test container from strong drafts at all times to prevent mechanical loss of the test specimen.

10.16 Cool in the desiccator, and record the weight, W_3 , of the crucible and acid-insoluble ash to the nearest 0.1 mg.

11. Calculation

11.1 If the biomass was prepared in accordance with Part B or C of Practice E 1757, calculate the percent acid-insoluble residue on a 105°C dry-weight basis as follows:

$$\% \text{ acid insoluble residue} \cdot \frac{W_2 - W_3}{W_1 \times \frac{T_{105}}{T_{prep}}} \times 100 \quad (1)$$

where:

- W_1 = initial sample weight,
- W_2 = weight of the crucible, acid-insoluble residue, and acid-insoluble ash,
- W_3 = weight of the crucible and acid-insoluble ash,
- T_{105} = % total solids determined at 105°C as determined in accordance with Test Method E 1756, and
- T_{prep} = % T_{fd} or % T_{45} as determined by Practice E 1757.

11.2 If the biomass was prepared in accordance with Part A of Practice E 1757 or in accordance with Test Method E 1756, calculate the percent acid-insoluble residue on a 105°C dry-weight basis as follows:

$$\% \text{ acid insoluble residue} = \frac{W_2 - W_3}{W_1 \times \frac{T_{105}}{100}} \times 100 \quad (2)$$

where:

- W_1 = initial sample weight,
- W_2 = weight of the crucible, acid-insoluble residue, and acid-insoluble ash,
- W_3 = weight of the crucible and acid-insoluble ash, and

T_{105} = %total solids determined at 105°C as determined in accordance with Test Method E 1756.

12. Report

12.1 Report the percent acid-insoluble residue, to two decimal places, on a 105°C dry-weight basis.

13. Precision and Bias

13.1 Precision:

13.1.1 Data obtained by replicate testing of a hybrid poplar in one laboratory yielded a standard deviation in Klason lignin content of 0.41 % and a CV % of 1.59 %.

13.1.2 Data obtained by replicate testing of a hybrid poplar sample in six different laboratories yielded a standard deviation of 2.37 % and a CV % of 9.92 %.

14. Keywords

14.1 acid-insoluble lignin; agricultural residue; biomass; fermentation residue; herbaceous; lignin; wastepaper; wood

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).