



Standard Test Methods for Analysis of Wood Fuels¹

This standard is issued under the fixed designation E 870; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

ε¹ NOTE—Section 7 on Keywords was added editorially in April 1998.

1. Scope

1.1 These test methods cover the proximate and ultimate analysis of wood fuels and the determination of the gross caloric value of wood fuels sampled and prepared by prescribed test methods and analyzed according to ASTM established procedures. Test methods as herein described may be used to establish the rank of fuels, to show the ratio of combustible to incombustible constituents, to provide the basis for buying and selling, and to evaluate for beneficiation or for other purposes.

1.2 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 1102 Test Method for Ash in Wood²

E 711 Test Method for Gross Calorific Value of Refuse-Derived Fuel By the Bomb Calorimeter³

E 775 Test Methods for Total Sulfur in the Analysis Sample of Refuse-Derived Fuel³

E 777 Test Method for Carbon and Hydrogen in the Analysis Sample of Refuse-Derived Fuel³

E 778 Test Methods for Nitrogen in the Analysis Sample of Refuse-Derived Fuel³

E 871 Method for Moisture Analysis of Particulate Wood Fuels³

E 872 Test Method for Volatile Matter in the Analysis of Particulate Wood Fuels³

3. Definitions

3.1 *proximate analysis*—an assay of the moisture, ash,

volatile matter, and fixed carbon as determined by prescribed test methods. Other constituents such as sulfur and phosphorus are not included.

3.2 *ultimate analysis*—the determination of carbon and hydrogen in the material, as found in the gaseous products of its complete combustion, the determination of sulfur, nitrogen, and ash in the material as a whole, and the calculation of oxygen by difference.

4. Significance and Use

4.1 These test methods of analysis described herein can be used for the proximate analysis, ultimate analysis, and the determination of the gross caloric value of wood fuels.

5. Procedure

5.1 *Moisture*—Method E 871.

5.2 *Ash*—Test Method D 1102.

5.3 *Volatile Matter*—Test Method E 872.

5.4 *Fixed Carbon*—The fixed carbon is a calculated value. It is the resultant of the summation of percentage moisture, ash, and volatile matter subtracted from 100. All percentages shall be on the same moisture reference base.

5.5 *Carbon and Hydrogen*—Test Method E 777.

5.6 *Sulfur*—Test Methods E 775.

5.7 *Nitrogen*—Test Methods E 778.

5.8 *Oxygen*—The oxygen is a calculated value. It is the resultant of the summation of percentages carbon, hydrogen, sulfur, nitrogen, and ash subtracted from 100. All percentages shall be on the same moisture reference base.

5.9 *Gross Calorific Value*—Test Method E 711.

6. Precision and Bias

6.1 The precision and bias of the test methods described herein are contained in these individual test methods.

7. Keywords

7.1 biomass; bulk density; densified particulate biomass; green tree chip; hogged fuel; particulate wood fuel; pellets; proximate; sawdust; ultimate; volatile matter

¹ These test methods are under the jurisdiction of ASTM Committee E-48 on Biotechnology and are the direct responsibility of Subcommittee E48.05 on Biomass Conversion Systems.

Current edition approved Nov. 26, 1982. Published January 1983.

² *Annual Book of ASTM Standards*, Vol 04.09.

³ *Annual Book of ASTM Standards*, Vol 11.05.

 **E 870**

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.