



Designation: C 1233 – 9803

Standard Practice for Determining Equivalent Boron Contents of Nuclear Materials¹

This standard is issued under the fixed designation C 1233; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This standard details a recommended practice for the calculation of the Equivalent Boron Content (EBC) values for elements that are of potential significance as thermal neutron poisons. The values are determined from a knowledge of the atomic weight of elements and the thermal neutron absorption cross section in barns. This practice is illustrated by using the EBC factors of Table 1 which are based on thermal neutron (2200 m/s) absorption cross sections. Other EBC factors may be used depending upon the actual neutron energy characteristics of the applicable reactor system.

1.2 The following elements do not require to be included in the EBC calculations, as their EBC factors are less than or equal to 0.0001.

| | | |
|-----------|------------|-----------|
| aluminum | fluorine | rubidium |
| barium | lead | silicon |
| beryllium | neon | tin |
| bismuth | oxygen | zirconium |
| carbon | magnesium | |
| cerium | phosphorus | |

Their contribution to the total poison effect is not considered significant.

2. Referenced Documents

2.1 ASTM Standards:

¹ This practice is under the jurisdiction of ASTM Committee C-26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C26.02 on Fuel and Fertile Material Specifications.

Current edition approved Aug. 10, 1998; 2003. Published November 1998; August 2003. Originally published as C 1233-93; approved in 1993. Last previous approved edition 1998 as C 1233-978.

TABLE 1 Equivalent Boron Content Factors

| Element | Neutron Absorption Cross Section ^A (Barns) at 2200 m/s | Atomic Mass ^B | EBC Factor |
|--------------|---|--------------------------|------------|
| Antimony | 5.1 ^C | 121.75 | 0.0006 |
| Argon | 0.68 | 39.95 | 0.0002 |
| Arsenic | 4.5 | 74.92 | 0.0008 |
| Boron | 764 ^D | 10.81 | 1.0000 |
| Bromine | 6.9 | 79.91 | 0.0012 |
| Cadmium | 2520 | 112.41 | 0.3172 |
| Calcium | 0.43 | 40.08 | 0.0002 |
| Cesium | 29 | 132.91 | 0.0031 |
| Chlorine | 33.5 | 35.45 | 0.0132 |
| Chromium | 3.07 | 52.00 | 0.0008 |
| Cobalt | 37.2 | 58.93 | 0.0089 |
| Copper | 3.78 | 63.54 | 0.0008 |
| Dysprosium | 940 | 162.50 | 0.0818 |
| Erbium | 159.2 | 167.26 | 0.0135 |
| Europium | 4565 | 151.97 | 0.4250 |
| Gadolinium | 48890 | 157.25 | 4.3991 |
| Gallium | 2.9 | 69.72 | 0.0006 |
| Germanium | 2.3 ^C | 72.59 | 0.0004 |
| Gold | 98.65 | 196.97 | 0.0071 |
| Hafnium | 104.1 | 178.49 | 0.0083 |
| Holmium | 64.7 | 164.93 | 0.0056 |
| Hydrogen | 0.33 | 1.01 | 0.0046 |
| Indium | 193.8 ^C | 114.82 | 0.0239 |
| Iodine | 6.2 | 126.90 | 0.0007 |
| Iridium | 425.30 | 192.22 | 0.0313 |
| Iron | 2.56 ^C | 55.85 | 0.0006 |
| Krypton | 25.00 | 83.80 | 0.0042 |
| Lanthanum | 8.97 ^C | 138.91 | 0.0009 |
| Lithium | 70.6 ^E | 6.94 | 0.1439 |
| Lutetium | 76.4 | 174.97 | 0.0062 |
| Manganese | 13.3 | 54.94 | 0.0034 |
| Mercury | 372.3 | 200.59 | 0.0263 |
| Molybdenum | 2.55 ^C | 95.94 | 0.0004 |
| Neodymium | 50.5 ^C | 144.24 | 0.0050 |
| Nickel | 4.49 ^C | 58.69 | 0.0011 |
| Niobium | 1.15 | 92.91 | 0.0002 |
| Nitrogen | 1.90 | 14.01 | 0.0019 |
| Osmium | 16.00 | 190.20 | 0.0012 |
| Palladium | 6.90 | 106.42 | 0.0009 |
| Platinum | 10.30 | 195.08 | 0.0007 |
| Potassium | 2.1 ^C | 39.10 | 0.0008 |
| Praseodymium | 11.5 | 140.91 | 0.0012 |
| Rhenium | 89.70 | 186.21 | 0.0068 |
| Rhodium | 145.20 | 102.91 | 0.0200 |
| Ruthenium | 2.56 ^C | 101.07 | 0.0004 |
| Samarium | 5670 | 150.36 | 0.5336 |
| Scandium | 27.20 | 44.96 | 0.0086 |
| Selenium | 11.70 | 78.96 | 0.0021 |
| Silver | 63.3 | 107.87 | 0.0083 |
| Sodium | 0.53 | 22.99 | 0.0003 |
| Strontium | 1.28 ^C | 87.62 | 0.0002 |
| Sulphur | 0.52 | 32.06 | 0.0002 |
| Tantalum | 20.6 | 180.95 | 0.0016 |
| Tellurium | 4.70 | 127.60 | 0.0005 |
| Terbium | 23.4 | 158.92 | 0.0021 |
| Thallium | 3.43 | 204.37 | 0.0002 |
| Thorium | 7.37 | 232.04 | 0.0004 |
| Thulium | 105 | 168.93 | 0.0088 |
| Titanium | 6.1 | 47.88 | 0.0018 |
| Tungsten | 18.4 | 183.85 | 0.0014 |
| Vanadium | 5.08 | 50.94 | 0.0014 |
| Xenon | 23.90 | 131.29 | 0.0026 |
| Ytterbium | 35.5 | 173.04 | 0.0029 |
| Yttrium | 1.28 | 88.91 | 0.0002 |
| Zinc | 1.11 | 65.39 | 0.0002 |

^A *Neutron Cross Sections*, Vol 1, Parts A and B, Academic Press, New York, 1981 and 1984, respectively.

^B Holden, N. E., and Martin, R. L., *Pure and Applied Chemistry*, Vol 56, p. 653, 1984.

^C In the absence of other data, the neutron capture cross section for a Maxwellian flux is used.

^D Cross section is primarily due to a single isotope, whose isotopic abundance is variable in nature. The value can vary between 733 and 779 barns depending upon the source. See Holden, N. E., *Neutron Capture Cross Section Standards for BNL-325*, Fourth Ed., BNL-NCS-51388, January 1981.

^E Cross section is primarily due to a single isotope, whose isotopic abundance is variable in nature. The value can vary between 69 and 72 barns depending upon the source. See Holden, N. E., *Neutron Capture Cross Section Standards for BNL-325*, Fourth Ed., BNL-NCS-51388, January 1981.

- C 696 Test Methods for Chemical, Mass Spectrometric, and Spectrochemical Analysis of Nuclear-Grade Uranium Dioxide Powders and Pellets²
- C 698 Test Methods for Chemical, Mass Spectrometric, and Spectrochemical Analysis of Nuclear-Grade Mixed Oxides ((U,Pu)O₂)²
- C 699 Methods for Chemical, Mass Spectrometric, and Spectrochemical Analysis of, and Physical Tests on, Beryllium Oxide Powder²
- C 761 Test Methods for Chemical, Mass Spectrometric, Spectrochemical, Nuclear, and Radiochemical Analysis of Uranium Hexafluoride²
- C 799 Test Methods for Chemical, Mass Spectrometric, Spectrochemical, Nuclear, and Radiochemical Analysis of Nuclear-Grade Uranyl Nitrate Solutions²
- C 859 Terminology Relating to Nuclear Materials²

3. Terminology

3.1 Terms shall be defined in accordance with Terminology C 859.

4. Methods For EBC Determination

4.1 Agreement shall be reached between the buyer and seller as to which elements shall be analyzed for calculation of their EBC. It is recommended that B, Cd, Dy, Eu, Sm, and Gd be included in this calculation. Analytical methods for such elements shall be those given in Methods C 696, C 699, and C 799, and Test Methods C 698 and C 761 as applicable or as otherwise agreed upon between buyer and seller.

4.2 The individual EBC values are calculated using the EBC factors from Table 1 as follows:

$$EBC \text{ of impurity} = (EBC \text{ factor})(\mu\text{g of impurity/g base material})$$

where:

$$EBC \text{ factor} = \frac{(atomic \text{ mass boron})(\sigma a \text{ impurity})}{(atomic \text{ mass impurity})(\sigma a \text{ boron}), \text{ and}}$$

σa = atomic neutron absorption cross section in barns.

The values given in Table 1 have been calculated using a value of 764 Barns for the neutron absorption cross section (σa) of boron. This value may vary in nature according to the isotopic composition of the elements. If an alternative value is chosen the EBC factors must be recalculated using the chosen value.

4.3 If the concentration of any of the elements used in the calculation is reported as “less than” values, these values shall be used in calculating the EBC.

4.4 A total EBC value, if required, is determined by the summation of individual EBC values.

4.5 Plutonium, thorium and uranium have not been included, as they are fissionable elements.

5. Keywords

5.1 boron; neutron absorption; nuclear materials; nuclear poisons

² Annual Book of ASTM Standards, Vol 12.01.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).