



**Designation: C 967 – 87 (Reapproved 1996)**

AMERICAN SOCIETY FOR TESTING AND MATERIALS  
100 Barr Harbor Dr., West Conshohocken, PA 19428  
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

## Standard Specification for Uranium Ore Concentrate<sup>1</sup>

This standard is issued under the fixed designation C 967; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

This specification is intended to provide the nuclear industry with a general standard for uranium ore concentrate. Material conforming to this specification will generally meet the requirements for conversion to uranium hexafluoride. However, the converter may relax or supplement this specification upon mutual agreement with the customer.

#### 1. Scope

1.1 This specification covers uranium ore concentrate containing a minimum of 65 weight % uranium.

1.2 This specification does not include requirements for health and safety. Observance of this specification does not relieve the user of the obligation to be aware of and conform to all applicable international, national, state, and local regulations pertaining to possessing, shipping, or using source nuclear material (see 2.2).

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

#### 2. Referenced Documents

##### 2.1 ASTM Standards:

C 859 Terminology Relating to Nuclear Materials<sup>2</sup>

C 1022 Test Methods for Chemical and Atomic Absorption Analysis of Uranium-Ore Concentrate<sup>2</sup>

C 1075 Practices for Sampling Uranium-Ore Concentrate<sup>2</sup>

##### 2.2 U.S. Government Documents:

Nuclear Materials Licensing Code of Federal Regulations (latest edition) Title 10, Chapter 1, Nuclear Regulatory Commission<sup>3</sup>

Nuclear Materials Licensing Code of Federal Regulations, Title 49, *Transportation* Chapter 1, Materials Transportation Bureau<sup>4</sup>

Nuclear Materials Licensing Code of Federal Regulations, Energy Part 50 (10CFR 50) Licensing of Domestic Production and Utilization Facilities<sup>3</sup>

##### 2.3 ANSI Standard:

ANSI/ASME NQA-1 Quality Assurance Requirements for Nuclear Facilities<sup>5</sup>

#### 3. Terminology Definitions

3.1 Except as otherwise defined herein, definitions of terms are as given in Terminology C 859.

#### 4. Chemical Composition

4.1 *Uranium Content*—The uranium content, as received, shall be a minimum of 65 weight %.

4.2 *Isotopic Content*—The isotopic content shall be that of naturally occurring uranium (0.7105 to 0.7115 % <sup>235</sup>U).

4.3 *Insoluble Uranium*—The uranium insoluble in nitric acid shall be a maximum of 0.10 weight % on a uranium basis.

4.4 *Extractable Organic*—The extractable organic shall be a maximum of 0.10 weight % on an as-received basis of an undried sample.

4.5 *Impurity Content*—The impurity content shall be less than the maximum limits specified in Table 1.

#### 5. Physical Properties

5.1 *Particle Size*—All of a representative sample (Section 6) shall pass through a sieve with an aperture of 6.35 mm (¼ in.).

5.2 *Ability to Flow*—Concentrate shall be sufficiently free-flowing to permit sampling.

5.3 *Foreign Matter*—Concentrate shall be free of all materials and objects that: (a) are not produced as a constituent of concentrates in the milling of uranium ore, or, (b) would or could be detrimental to the sampling of concentrates or to the equipment used in such sampling.

#### 6. Sampling

6.1 The lot size and number of tests (and retests when required) shall be as mutually agreed.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C-26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C26.02 on Fuel and Fertile Material Specifications.

Current edition approved May 29, 1987. Published July 1987. Originally published as C 967 – 81. Last previous edition C 967 – 81.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 12.01.

<sup>3</sup> Available from the Nuclear Regulatory Commission, 1717 H Street, N. W., Washington, DC 20555.

<sup>4</sup> Available from the Materials Transportation Bureau, 400 Seventh St., Washington, DC, 20590.

<sup>5</sup> Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

**TABLE 1 Impurities and Maximum Concentration Limits**

Impurity	Maximum Concentration Limit (Wt %, Uranium Basis) <sup>A</sup>	
	Limit Without Penalty <sup>B</sup>	Limit Without Rejection <sup>C</sup>
As	0.05	0.10
B	0.005	0.10
Ca	0.05	1.00
Carbonate (calculated as CO <sub>3</sub> )	0.20	0.50
F	0.01	0.10
Halogens <sup>D</sup>	0.05	0.10
Fe	0.15	1.00
Mg	0.02	0.50
Moisture <sup>E</sup>	2.0	5.0
Mo	0.10	0.30
P	0.10	0.70
K	0.20	3.00
Si(calculated as SiO <sub>2</sub> )	0.50	2.5
Na	0.50	7.50
S	1.00	4.00
Th	1.00	2.50
Ti	0.01	0.05
V	0.06	0.30
Zr	0.01	0.10

<sup>A</sup>Except as specified otherwise.

<sup>B</sup>Surcharges may apply to concentrate having impurities exceeding these limits, or

<sup>C</sup>As otherwise agreed upon between purchaser and seller.

<sup>D</sup>Exclusive of fluorine.

<sup>E</sup>As determined by the sampling facility.

6.2 A representative sample, of a size sufficient to perform the tests prescribed in Sections 4 and 5, shall be taken from each lot.

6.3 Practices C 1075 is referenced as a guide.

## 7. Test Methods

7.1 All chemical analyses shall be performed on portions of the representative sample prepared in accordance with Section 6. Analytical chemistry methods shall be as mutually agreed.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*

7.2 Test Methods C 1022 is referenced as a guide.

## 8. Certification

8.1 When specified in the purchase order or contract, certification shall be furnished that the material was sampled and tested in accordance with this specification and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

## 9. Packaging and Package Marking

9.1 Uranium ore concentrate shall be packaged and shipped in drums having lids fitted with watertight sealing rings. The lids shall be attached to the drums in a manner that minimizes loss of concentrate in the event of mishandling. Shipping containers shall meet applicable regulatory requirements. CFR Title 10 and Title 49 are referenced as guides.

9.2 Each container shall bear, as a minimum, labels on the lid and side with the following information:

- 9.2.1 Seller's name,
- 9.2.2 Material in containers,
- 9.2.3 Lot number,
- 9.2.4 Gross, tare and net weights, and
- 9.2.5 Container ( ) of ( ).

## 10. Quality Assurance

10.1 Quality assurance requirements shall be as agreed upon between the buyer and the seller when specified in the purchase order. Code of Federal Regulations Title 10, Part 50, Appendix B and NQA-1 are referenced as guides.

## 11. Keywords

- 11.1 concentrates; uranium ore; yellow cake