



Standard Classification of Alumina and Alumina-Silicate Castable Refractories¹

This standard is issued under the fixed designation C 401; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This classification pertains to alumina and alumina-silicate castable refractories that, when tempered with water, will develop structural strength by chemical action.

1.2 The values in inch-pound units are to be regarded as the standard. The values in parentheses are provided for information only.

1.3 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

C 113 Test Method for Reheat Change of Refractory Brick²

C 133 Test Methods for Cold Crushing Strength and Modulus of Rupture of Refractories²

C 134 Test Methods for Size, Dimensional Measurements, and Bulk Density of Refractory Brick and Insulating Firebrick²

C 862 Practice for Preparing Refractory Concrete Specimens by Casting²

C 865 Practice for Firing Refractory Concrete Specimens²

3. Significance and Use

3.1 Alumina and alumina-silicate castable refractories are produced to yield property characteristics commensurate with different end use properties. Volume stability, modulus of rupture, bulk density, and lime content have become useful measures to distinguish various alumina and alumina-silicate castable formulations for initial fitness for service. This classification is considered useful for purchase specifications and for quality control.

4. Basis of Classification

4.1 *Regular Castable Refractories*—This class includes alumina and alumino-silicate castable refractories which contain hydraulic-setting cement and which have a total lime (CaO) content greater than 2.5 % on a calcined basis. Under this class, castables having a modulus of rupture after drying of at least 300 psi (2.07 MPa) are normal-strength, and those having at least 600 psi (4.14 MPa) modulus of rupture are high-strength types. They are further classified on the basis of volume stability of cast test brick when fired at the temperatures prescribed in Table 1.

4.2 *Low-Cement Castable Refractories*—This class includes alumina and alumino-silicate castable refractories which contain hydraulic-setting cement and which have a total lime (CaO) content of greater than 1.0 to 2.5 % on a calcined basis.

4.3 *Ultra-Low Cement Castable Refractories*—This class includes alumina and alumino-silicate castable refractories which contain hydraulic-setting cement and which have a total lime (CaO) content of greater than 0.2 to 1.0 % on a calcined basis.

4.4 *No-Cement Castable Refractories*—This class includes alumina and alumino-silicate castable refractories which do not contain hydraulic-setting cement and in which the bonding agent(s) contribute no significant amount of lime (CaO). The product might contain up to 0.2 % total lime (CaO) on a calcined basis as contributed by the aggregate.

4.5 *Insulating Castable Refractories*—This class includes insulating castable refractories which are classified on the basis of bulk density of dried cast test brick and volume stability of such test brick when fired at the temperatures prescribed in Table 2.

5. Test Methods

5.1 The properties enumerated in this classification shall be determined in accordance with the following ASTM methods:

5.1.1 *Modulus of Rupture*—Test Methods C 133 on test brick with Practice C 862, and after oven-drying in accordance with the Curing of Test Specimens section of Practice C 862. Specimens should be fired as given in heating schedule of Practice C 865.

¹ This classification is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.92 on The Joseph E. Kopanda Subcommittee for Editorial, Terminology and Classification.

Current edition approved Jan. 25, 1991. Published July 1991. Originally published as C 401 – 57 T. Last previous edition C 401 – 89.

² *Annual Book of ASTM Standards*, Vol 15.01.

TABLE 1 Regular Castable Refractories

Test Requirements	Classes of Alumina-Silica Base Castable Refractories						
	Class A	Class B	Class C	Class D	Class E	Class F	Class G
Permanent linear shrinkage, not more than 1.5 % when fired for 5 h at	2000°F (1095°C)	2300°F (1260°C)	2500°F (1370°C)	2700°F (1480°C)	2900°F (1595°C)	3100°F (1705°C)	3200°F (1760°C)

**TABLE 2 Insulating Castable Refractories
(Refer to 4.5)**

Test Requirements	Classes of Insulating Castable Refractories				
	Class N	Class O	Class P	Class Q	Class R
Permanent linear shrinkage, not more than 1.5 % when fired for 5 h at	1700°F (925°C)	1900°F (1040°C)	2100°F (1150°C)	2300°F (1260°C)	2500°F (1370°C)
Maximum bulk density, lb/ft ³ (g/cm ³) after drying at 220 to 230°F (105 to 110°C)	55 (0.88)	65 (1.04)	75 (1.20)	90 (1.44)	95 (1.52)
	Class S	Class T	Class U	Class V	
Permanent linear shrinkage, not more than 1.5 % when fired for 5 h at	2700°F (1480°C)	2900°F (1595°C)	3000°F (1650°C)	3200°F (1760°C)	
Maximum bulk density, lb/ft ³ (g/cm ³) after drying at 220 to 230°F (105 to 110°C)	95 (1.52)	100 (1.60)	105 (1.68)	105 (1.68)	

5.1.2 *Permanent Linear Shrinkage*—Test Method C 113 on specimens prepared in accordance with Practice C 862 and fired as given in heating schedule of Practice C 865.

5.1.3 *Bulk Density*—Test Methods C 134 on test brick prepared and oven-dried in accordance with Practice C 862 and fired as given in heating schedule of Practice C 865.

6. Retests

6.1 Because of variables resulting from sampling and the lack of satisfactory reproducibility in tests conducted by different laboratories, the material may be resampled and retested when requested by either the manufacturer or the

purchaser. This may apply in instances when the first test results do not conform to the requirements prescribed in this classification. The final results to be used shall be the average of at least two sets of results, each of which has been obtained by following in detail the specified testing procedures.

7. Keywords

7.1 alumina; alumina-silicate; castable refractories; insulating castable refractories; low-cement castable refractories; no-cement castable refractories; regular castable refractories; ultra-low cement castable refractories

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).