



Standard Classification of Chrome Brick, Chrome-Magnesia Brick, Magnesia-Chrome Brick, and Magnesia Brick¹

This standard is issued under the fixed designation C 455; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification categorizes machine-made refractory brick defined as chrome brick, chrome-magnesia brick, magnesia-chrome brick, and magnesia brick (see 3.1). It does not cover products made from electrically fused magnesium oxide or to products made by fusion casting. Its purpose is to describe classes distinguished by obvious differences in magnesium oxide (MgO) content except for chrome brick.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

C 71 Terminology Relating to Refractories²

NOTE 1—Chemical analysis of refractory products are determined by a combination of x-ray fluorescence (XRF) and inductively coupled plasma (ICP) using standard reference materials (SRM), including various types of minerals and refractory materials which are available from the National Institute of Standards and Technology and other appropriate sources.

3. Terminology

3.1 For definitions of terms used in this classification, see Terminology C 71.

4. Significance and Use

4.1 This classification categorizes the defined types of refractory brick, with the exception of chrome brick, into

distinct classes based on a nominal and minimal value for magnesium oxide content. Chrome brick are treated as a separate class without reference to magnesium oxide content. Such classes have historically been generally useful in relating the defined types to specific industrial applications and in developing product or purchasing specifications.

5. Basis of Classification

5.1 Chrome-magnesia brick, magnesia-chrome brick, and magnesia brick are classified by MgO content as shown in Table 1. Chrome brick is not classified by MgO content (see Table 1).

6. Test Methods

6.1 The determination of MgO on an ignited basis as required by this classification shall be determined by a combination of x-ray fluorescence (XRF) and inductively coupled plasma (ICP) using standard reference materials (SRM), including various types of minerals and refractory materials which are available from the National Institute of Standards and Technology and other appropriate sources.

7. Retests

7.1 Because of variables resulting from sampling and the lack of satisfactory reproducibility in tests conducted by different laboratories, the material may be resampled and retested when requested by either the manufacturer or the purchaser. This may apply in instances when the first test results do not conform to the requirements prescribed in this classification. The final results to be used shall be the average of at least two sets of results, each of which has been obtained by following in detail the specified testing procedures.

8. Keywords

8.1 brick; chrome; classification; magnesium oxide; magnesia; MgO; refractories

¹ This classification is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.92 on The Joseph E. Kopanda Subcommittee for Editorial, Terminology and Classification.

Current edition approved Nov. 10, 1997. Published December 1998. Originally published as C 455 – 60 T. Last previous edition C 455 – 84 (1992) ^{ε1}.

² *Annual Book of ASTM Standards*, Vol 15.01.

TABLE 1 Classification of Chrome Brick,^A Chrome-Magnesia Brick, Magnesia-Chrome Brick, and Magnesia Brick According to MgO Content

Class	MgO Content, % ^B	
	Nominal	Minimum
Chrome-Magnesia and Magnesia-Chrome Brick ^C		
30	30	25
40	40	35
50	50	45
60	60	55
70	70	65
80	80	75
Magnesia Brick ^C		
90	90	86
95	95	91
98	98	96

^A Chrome brick—a refractory brick, which may be burned or unburned, manufactured predominately or entirely of refractory-grade chrome ore.

^B Ignited basis.

^C This classification applies to both chemically bonded and burned brick.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).