

This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: C 502 – 93a (Reapproved 1999)



Designation: C 502 – 04

Standard Test Method for Wedging of Flat, Rectangular Ceramic Wall and Floor Tile¹

This standard is issued under the fixed designation C 502; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

¹ This method is under the jurisdiction of ASTM Committee C-21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved ~~Aug. 15, 1993~~ April 1, 2004. Published ~~October 1993~~ May 2004. Originally published as C 502 – 62 T, approved 1962. Last previous edition approved in 1999 as C 502 – 93a (1999).

1. Scope

1.1 This test method covers the determination of the wedging or deviation from rectangularity of flat, rectangular wall and floor tile. The test method covers tile as defined in Terminology C 242.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C 242 Terminology of Ceramic Whitewares and Related Products

C 499 Test Method for Facial Dimensions and Thickness of Flat, Rectangular Ceramic Wall and Floor Tile

3. Terminology

3.1 *Definitions:*

3.1.1 *wedging of tile*—the difference between two spaced measurements of the length or width of a tile, expressed as a percentage of the distance between points of measurements.

3.2 For the definition of major and minor facial dimensions see Test Method C 499.

4. Significance and Use

4.1 Tile are normally pressed in dies having true 90° angle construction. However, minor variations in die fill, compacting pressure, and heat treatment can result in finished tile with acute and obtuse angles. This out-of-squareness results in a difference in length of opposite sides, and the tile may have the appearance of a keystone or wedge.

4.2 Excessive wedging presents difficulties in the installation of tile. This test method provides a means for determining the degree of wedging.

5. Apparatus

5.1 An apparatus as shown in Fig. 1 or other suitable apparatus. The dial gage (B) is used for measuring rectangularity.

5.2 A calibrating plate made of steel or aluminum of accurate dimensions and with straight, flat sides.

6. Test Specimens

6.1 ~~At least five tile specimens shall be selected at random from the lot to be tested. For items smaller than 6 in.² (38.7 cm²) in facial area, at least ten specimens shall be used. For items 6 in.² in facial area or larger, at least five specimens shall be used.~~ The specimens shall be brushed to remove all adhering particles of clay and sand.

7. Procedure

7.1 Select an apparatus of the appropriate dimensions so that, when a tile is placed in the apparatus, the locating studs are 5 mm from each corner of the side adjacent to the side being measured. The plunger of the dial gage (B) shall also be 5 mm from the corner of the tile on the side being measured.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards*, Vol 15.02, Standards volume information, refer to the standard's Document Summary page on the ASTM website.




FIG. 1 Apparatus for Measurement of Straightness of Sides and Rectangularity

7.2 Fit the appropriate calibrating plate exactly into position on the instrument and adjust the dial gauge reading to a suitable known value.

7.3 Remove the calibrating plate, place the proper surface of the tile on the locating studs in the apparatus, and record the dial gauge reading 5 mm from the corner. Rotate the tile, if square, to obtain four measurements. Repeat this procedure for each tile. In the case of oblong tiles, use separate instruments of the appropriate dimensions to measure lengths and widths. Measure to an accuracy of 0.1 mm.

8. Calculation

8.1 Calculate the percentage of wedging or deviation from rectangularity as follows:

$$\frac{d}{L} \times 100 = \% \quad (1)$$

where:

L = length of the adjacent side of the tile and

d = deviation of the outer corner of the side of the tile (measured 5 mm from the corner) from the inner side of the calibrating plate.

9. Report

9.1 The report shall give the type and number of tile tested and shall show for each specimen:

9.1.1 Average, maximum, and minimum percentage of wedging of the major lengths,

9.1.2 Average, maximum, and minimum percentage of wedging of the major widths,

9.1.3 Average, maximum, and minimum percentage of wedging of the minor lengths, and

9.1.4 Average, maximum, and minimum percentage of wedging of the minor widths.

NOTE 1—For nominally square tile, 9.1.2 and 9.1.4 are not given and 9.1.1 and 9.1.3 for such tile are calculated from the maximum difference among the four measurements.

10. Precision and Bias

10.1 Precision is being determined.

10.2 Bias depends almost entirely on the accuracy of the measuring devices and care taken to set up the equipment. No interlaboratory data are available with which to estimate a bias.

11. Keywords

11.1 flat, rectangular ceramic wall and floor tile; wedging

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).