



Standard Test Method for Heat of Ablation¹

This standard is issued under the fixed designation E 458; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers determination of the heat of ablation of materials subjected to thermal environments requiring the use of ablation as an energy dissipation process. Three concepts of the property are described and defined: cold wall, effective, and thermochemical heat of ablation.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- E 285 Test Method for Oxyacetylene Ablation Testing of Thermal Insulation Materials²
- E 341 Practice for Measuring Plasma Arc Gas Enthalpy by Energy Balance²
- E 377 Practice for Internal Temperature Measurements in Low Conductivity Materials²
- E 422 Test Method for Measuring Heat Flux Using a Water-Cooled Calorimeter²
- E 457 Test Method for Measuring Heat-Transfer Rate Using a Thermal Capacitance (Slug) Calorimeter²
- E 459 Test Method for Measuring Heat-Transfer Rate Using a Thin-Skin Calorimeter²
- E 470 Method for Measuring Gas Enthalpy Using Calorimetric Probes³
- E 471 Test Method for Obtaining Char Density Profile of Ablative Materials by Machining and Weighing²
- E 511 Test Method for Measuring Heat Flux Using a Copper-Constantan Circular Foil, Heat-Flux Gage²

3. Terminology

3.1 Descriptions of Terms Specific to This Standard:

3.1.1 *heat of ablation*—a property that indicates the ability of a material to provide heat protection when used as a sacrificial thermal protection device. The property is a function

of both the material and the environment to which it is subjected. In general, it is defined as the incident heat dissipated by the ablative material per unit of mass removed, or

$$Q^* = q/m \quad (1)$$

where:

- Q^* = heat of ablation, kJ/kg,
- q = incident heat transfer rate, kW/m², and
- m = total mass transfer rate, kg/m²·s.

3.2 The heat of ablation may be represented in three different ways depending on the investigator's requirements:

3.3 *cold-wall heat of ablation*—The most commonly and easily determined value is the cold-wall heat of ablation, and is defined as the incident cold-wall heat dissipated per unit mass of material ablated, as follows:

$$Q^* = q_{cw}/m \quad (2)$$

where:

- Q^*_{cw} = cold-wall heat of ablation, kJ/kg,
- q_{hw} = heat transfer rate from the test environment to a cold wall, kW/m², and
- m = total mass transfer rate, kg/m²·s.

The temperature of the cold-wall reference for the cold-wall heat transfer rate is usually considered to be room temperature or close enough such that the hot-wall correction given in Eq 7 is less than 5 % of the cold-wall heat transfer rate.

3.4 *effective heat of ablation*—The effective heat of ablation is defined as the incident hot-wall dissipated per unit mass ablated, as follows:

$$Q^*_{eff} = q_{hw}/m \quad (3)$$

where:

- Q^*_{eff} = effective heat of ablation, kJ/kg,
- q_{hw} = heat transfer rate from the test environment to a nonablating wall at the surface temperature of the material under test, kW/m², and
- m = total mass transfer rate, kg/m²·s.

3.5 *thermochemical heat of ablation*—The thermochemical heat of ablation is defined as the incident hot-wall heat dissipated per unit mass ablated, corrected for reradiation heat rejection processes and material eroded by mechanical removal, as follows:

$$Q^*_{tc} = (q_{hw} - q_{rr} - q_{mech})/m_{tc} \quad (4)$$

¹ This test method is under the jurisdiction of ASTM Committee E21 on Space Simulation and Applications of Space Technology and is the direct responsibility of Subcommittee E21.08 on Thermal Protection.

Current edition approved Aug. 29, 1972. Published November 1972.

² *Annual Book of ASTM Standards*, Vol 15.03.

³ Discontinued, see 1982 *Annual Book of ASTM Standards*, Part 41.



$$m_{tc} = m - m_{mech} \quad (5)$$

$$q_{mech} = m_{mech} (h_m) \quad (6)$$

where:

- Q_{tc}^* = thermochemical heat of ablation, kJ/kg,
 q_{rr} = reradiative heat transfer rate, kW/m²,
 m_{tc} = mass transfer rate due to thermochemical processes, kg/m²·s,
 m_{mech} = mass-transfer rate due to mechanical processes, kg/m²·s,
 q_{mech} = heat-transfer rate due to energy carried away with mechanically removed material, kW/m², and
 h_m = enthalpy of mechanically removed material, kJ/kg.

Mechanical removal of material takes place in the more severe test environments where relatively high aerodynamic shear or particle impingement is present. The effects of mechanical removal and theories relating to the mechanism of this process are presented in Refs (1-5).⁴ If the effects of mechanical removal of material cannot be determined or are deemed unimportant, the term q_{mech} in Eq 4 goes to zero. The investigator should, however, be aware of the existence of this phenomenon and also note whether this effect was considered when reporting data.

3.6 The three heat of ablation values described in 3.2 require two basic determinations: the heat-transfer rate and the mass-transfer rate. These two quantities then assume various forms depending on the particular heat of ablation value being determined.

4. Significance and Use

4.1 The heat of ablation provides a measure of the ability of a material to serve as a heat protection element in a severe thermal environment. The property is a function of both the material and the environment to which it is subjected. It is therefore required that laboratory measurements of heat of ablation simulate the service environment as closely as possible. Some of the parameters affecting the property are pressure, gas composition, heat transfer rate, mode of heat transfer, and gas enthalpy. As laboratory duplication of all parameters is usually difficult, the user of the data should consider the differences between the service and the test environments. Screening tests of various materials under simulated use conditions may be quite valuable even if all the service environmental parameters are not available. These tests are useful in material selection studies, materials development work, and many other areas.

5. Determination of Heat Transfer Rate

5.1 Cold-Wall Heat Transfer Rate:

5.1.1 Determine the cold-wall heat-transfer rate to a specimen by using a calorimeter. These instruments are available commercially in several different types, some of which can be readily fabricated by the investigator. Selection of a specific type is based on the test configuration and the methods used,

and should take into consideration such parameters as instrument response time, test duration, and heat transfer rate (6).

5.1.1.1 The calorimeters discussed in 5.1.1 measure a “cold-wall” heat-transfer rate because the calorimeter surface temperature is much less than the ablation temperature. The value thus obtained is used directly in computing the cold-wall heat of ablation.

5.1.2 Install the calorimeter in a calorimeter body that duplicates the test model in size and configuration. This is done in order to eliminate geometric parameters from the heat-transfer rate measurement and to ensure that the quantity measured is representative of the heat-transfer rate to the test model. If the particular test run does not allow an independent heat-transfer rate measurement, as in some nozzle liner and pipe flow tests, mount the calorimeter as near as possible to the location of the mass-loss measurements. Take care to ensure that the nonablating calorimeter does not affect the flow over the area under test. In axisymmetric flow fields, measurements of mass loss and heat-transfer rate in the same plane, yet diametrically opposed, should be valid.

5.2 Computation of Effective and Thermochemical Heats of Ablation:

5.2.1 In order to compute the effective and thermochemical heats of ablation, correct the cold-wall heat-transfer rate for the effect of the temperature difference on the heat transfer. This correction factor is a function of the ratio of the enthalpy potentials across the boundary layer for the hot and cold wall as follows:

$$q_{hw} = q_{cw} [(h_e - h_{hw})/(h_e - h_{cw})] \quad (7)$$

where:

- h_e = gas enthalpy at the boundary layer edge, kJ/kg,
 h_{hw} = gas enthalpy at the surface temperature of the test model, kJ/kg, and
 h_{cw} = gas enthalpy at a cold wall, kJ/kg.

5.2.2 This correction is based upon laminar flow in air and subject to the restrictions imposed in Ref (7). Additional corrections may be required regarding the effect of temperature on the transport properties of the test gas. The form and use of these corrections should be determined by the investigator for each individual situation.

5.3 Gas Enthalpy Determination:

5.3.1 The enthalpy at the boundary layer edge may be determined in several ways: energy balance, enthalpy probe, spectroscopy, etc. Details of the methods may be found elsewhere (8-11). Take care to evaluate the radial variation of enthalpy in the nozzle. Also, in low-density flows, consider the effect of nonequilibrium on the evaluation. Determination of the gas enthalpy at the ablator surface and the calorimeter surface requires pressure and surface temperature measurements. The hot-wall temperatures are generally measured by optical methods such as pyrometers, radiometers, etc. Other methods such as infrared spectrometers and monochromators have been used (12,13). Effects of the optical properties of the boundary layer of an ablating surface make accurate determinations of surface temperature difficult.

5.3.2 Determine the wall enthalpy from the assumed state of the gas flow (equilibrium, frozen, or nonequilibrium), if the pressure and the wall temperature are known. It is further

⁴ The boldface numbers in parentheses refer to the references listed at the end of the standard.

assumed that the wall enthalpy is the enthalpy of the freestream gas, without ablation products, at the wall temperature. Make the wall static pressure measurements with an ordinary pitot arrangement designed for the flow regime of interest and by using the appropriate transducers.

5.4 Reradiation Correction:

5.4.1 Calculate the heat-transfer rate due to reradiation from the surface of the ablating material from the following equation:

$$q_{rr} = \epsilon \sigma T_s^4 \quad (8)$$

where:

- σ = Stefan-Boltzmann constant,
- T_s = absolute surface temperature of ablating material, K, and
- ϵ = thermal emittance of the ablating surface.

5.4.2 Eq 8 assumes radiation through a transparent medium to a blackbody at absolute zero. Consider the validity of this assumption for each case and if the optical properties of the boundary layer are known and are deemed significant, or the absolute zero blackbody sink assumption is violated, consider these effects in the use of Eq 8.

5.5 Mechanical Removal Correction:

5.5.1 Determine the heat-transfer rate due to the mechanical removal of material from the ablating surface from the mass-loss rate due to mechanical processes and the enthalpy of the material removed as follows:

$$q_{mech} = m_{mech} h_m \quad (9)$$

5.5.2 Approximate the enthalpy of the material removed by the product of the specific heat of the mechanically removed material, and the surface temperature (1-5).

6. Determination of Mass-Transfer Rate

6.1 The determination of the heat of ablation requires the measurement of the mass-transfer rate of the material under test. This may be accomplished in several ways depending on the type of material under test. The heat of ablation value can be affected by the choice of method.

6.1.1 Ablation Depth Method:

6.1.1.1 The simplest method of measurement of mass-loss rate is the change in length or ablation depth. Make a pretest and post-test measurement of the length and calculate the mass-loss rate from the following relationship:

$$m = \rho_o (\delta L / t) \quad (10)$$

where:

- ρ_o = virgin material density, kg/m³,
- δL = change in length or ablation depth, m, and
- t = test time, s.

6.1.1.2 Determine the change in length with the time of a model under test, by using motion picture techniques. Note that observation of the front surface alone does not, however, verify the existence of steady state ablation. Take care, however, to provide appropriate reference marks for measuring the length change from the film. Timing marks on the film are also required to accurately determine the time parameter. Avoid using framing speed as a reference, as it generally does not

provide the required accuracy.

6.1.1.3 Use the length change measurement of mass-loss rate for non-charring ablators, subliming materials, or with charring ablators under steady state ablation conditions (see Section 7) and only with materials that do not swell or grow in length.

6.1.2 Direct Weighing Method:

6.1.2.1 A second method of determining mass-transfer rate is by the use of a pretest and post-test mass measurement. This procedure yields the mass transfer rate directly. A disadvantage of this method is that the mass-transfer rate obtained is averaged over the entire test model heated area. The heat-transfer rate is generally varying over the surface and therefore leads to errors in heat of ablation. The mass-transfer rate is also averaged over the insertion period which includes the early part of the period when the ablation process is transient and after the specimen has been removed where some mass loss occurs. The experimenter should be guided by Section 7 in determining the magnitude of these effects.

6.1.2.2 In cases where the mass loss is low, the errors incurred in mass loss measurements could become large. It is therefore recommended that a significant mass loss be realized to reduce measurement errors. The problem is one of a small difference of two large numbers.

6.1.3 Core Sample Method:

6.1.3.1 Accomplish direct measurement of the mass loss by coring the model after testing by using standard core drills. The core size is determined by the individual experiment; however, core diameters of 5.0 to 10.0 mm should be adequate. Coring the model at the location of the heat-transfer rate measurement makes the mass-transfer rate representative of the measured environment. Obtain the mass-transfer rate from the core sample as follows:

$$m = (\rho_o V_o - w_f) / (t A_c) \quad (11)$$

where:

- V_o = original calculated volume of core, m³,
- w_f = final mass of core, kg, and
- A_c = cross-sectional area of core, m².

6.1.3.2 Calculate the original core volume using the measured diameter of the core after removal from the test model. The core drill dimensions should not be used due to drilling inaccuracies.

6.1.4 *Shrouded Core Method*—A second core sample method used in measuring ablation properties of materials involves the use of a model that includes a core and model shroud of the same material where the core has been prepared prior to testing. This method is described in detail in Ref. (5). This type of test model offers the advantages of ease of installation of thermal instrumentation, and direct pretest mass and dimensional measurements of the core. Calculate the heat of ablation in the same manner for the drilled core sample (6.1.3.2).

6.1.5 Core sample methods are useful with charring ablators, or materials that swell or grow on heating. The resulting core sample is also useful in observing the composition and formation of the char layer.

7. Steady-State Conditions

7.1 *General*—The nature of the definition of heat of ablation requires steady-state conditions. Variances from steady-state may be required in certain circumstances; however, it must be realized that transient phenomena make the values obtained functions of the test duration and therefore make material comparisons difficult.

7.2 Temperature Requirements:

7.2.1 In a steady-state condition, the temperature propagation into the material will move at the same velocity as the gas-ablation surface interface. A constant distance is maintained between the ablation surface and the isotherm representing the temperature front. Under steady-state ablation the mass loss and length change are linearly related.

$$mt = \rho_o \Delta_L + (\rho_o - \rho_c) \delta_c \quad (12)$$

where:

ρ_c = char density, kg/m³, and

δ_c = char depth, m.

7.2.2 This relationship may be used to verify the existence of steady-state ablation in the tests of charring ablators.

7.3 *Exposure Time Requirements*—The exposure time required to achieve steady-state may be determined experimentally by the use of multiple models by plotting the total mass loss as a function of the exposure time. The point at which the curve departs significantly from linearity is the minimum exposure time required for steady-state ablation to be established. Cases exist, however, in the area of very high heating rates and high shear where this type of test for steady-state may not be possible.

8. Apparatus

8.1 *Environmental*—The primary apparatus required is a means of providing the required thermal environment. Several devices have been used to accomplish this task including arc powered plasma jets, oxy-acetylene torch heaters (see Test Method E 285) liquid and solid propellant rocket exhausts, radiant heating lamps, etc. Each type of test facility has certain advantages and capability limitations and the type used will depend on the required test environment. The test facility used should be thoroughly described as part of the test report.

8.2 *Instrumentation*—The measurement apparatus such as calorimeters, enthalpy probes, temperature measuring devices, and instrumentation for enthalpy and pressure measurement of the test environment have been described in other ASTM standards (see Section 2). A description of all primary instrumentation should be included in the test report.

9. Test Specimen or Model

9.1 The test specimen size and shape will depend on the apparatus used, the desired results, service conditions, and type of test. Details of the specimen should be included as part of the test report.

10. Procedure

10.1 The exact procedure followed will depend on the heat source used, test specimen configuration and test objectives. A sample procedure is presented in the following paragraphs.

10.1.1 Weigh and measure the test specimen. Do not include

any supporting devices that are easily removed, both before and after test, in the mass measurement, in order to reduce the tare. For hygroscopic materials or chars, or both, the mass measurements before and after the test should be made under conditions of equal humidity (5). The important linear dimension is that parallel to the expected recession. Take both measurements such that the final length and mass change will be accurate to 2 %.

10.1.2 Energize the heat source and bring it to the required test condition. Verify the test condition by measuring the cold-wall heat-transfer rate, surface and pitot pressure, and gas enthalpy. Expose the diagnostic probes for sufficient length of time, so as to allow full instrument response and the equilibration of any transients induced by the probe insertion process.

10.1.2.1 After verification of the test condition, insert the material specimen in the test environment and expose it for a predetermined test time or until the test objectives have been accomplished. Insertion and retraction times should be short with respect to the test duration, of the order of 5 % or less of the total test time.

10.1.2.2 In certain char forming materials, take care so that the retraction dynamics do not disturb the fragile char. In the case of fragile char, it is sometimes desirable to terminate the test by extinguishing the heat source rather than by retracting the test specimen.

10.1.2.3 During the test period, take measurements of the specimen surface temperature for calculation of Q_{eff}^* and Q_{ic}^* , internal temperatures, and any other measurements required by the test objective.

10.1.2.4 After the test specimen is allowed to cool for handling, take post-test mass and length measurements. Take care in order to preserve the char structure. Take a still photograph of the specimen and include it in the report.

10.1.2.5 Evaluate variations from this test procedure as to their conformance to the steady-state concepts.

11. Calculation

11.1 Calculate the mass loss in two ways, length change and mass loss. Mass loss may be a gross mass loss from the entire test specimen, if heating rates are constant. Use the core sample method described in 6.1.4 in the case of a distribution of heat-transfer rates over the specimen. The appropriate method of determining mass loss will be selected by the investigator.

11.1.1 The mass-transfer rate is equal to the initial mass minus the final mass divided by the test duration. The proper area, over which the mass loss is measured, must be included.

$$m = (w_i - w_f)/tA_c \quad (13)$$

where:

w_i = initial mass of specimen or core, kg,

w_f = final mass of specimen or core, kg, and

A_c = area of specimen or cross-sectional area of core, m².

11.1.2 Calculate the mass-transfer rate from the length change as follows:

$$m = (L_i - L_f)(\rho_o/v) \quad (14)$$

where:

L_i = initial length, m, and

L_f = final length, m.

11.1.3 Compare these two mass-transfer rate values and account for any differences such as swelling of the material or handling damage. Use the value most representative of the test conditions and objectives in the calculation of heat of ablation.

11.1.4 Large discrepancies in these two measurements may indicate that the ablation process was transient and the steady-state definitions of heat of ablation are not applicable. It may also indicate that a significant char layer is present and the density change of this layer must be considered.

12. Report

12.1 Report the following information:

12.1.1 Material description,

12.1.2 Specimen size and configuration,

12.1.3 Test environmental conditions:

12.1.3.1 Gas composition,

12.1.3.2 Pressures,

12.1.3.3 Flow conditions, (mach number, laminar or turbulent free jet or channel, and so forth),

12.1.3.4 Gas enthalpy,

12.1.4 Test equipment and instrumentation description:

12.1.4.1 Heating device (type, dimensions, and so forth),

12.1.4.2 Calorimetry equipment,

12.1.4.3 Enthalpy measurement technique,

12.1.4.4 Radiation and optical equipment,

12.1.4.5 Other,

12.1.5 Specimen data:

12.1.5.1 Q_{cw}^* , Q_{eff}^* , or Q_{tc}^* , or a combination thereof,

12.1.5.2 Mass loss measurements,

12.1.5.3 Dimensional change measurements,

12.1.5.4 Test duration,

12.1.5.5 Other pertinent data,

12.1.6 Analysis of results, and

12.1.7 Photographs, temperature plots, and other supporting data.

13. Keywords

13.1 ablation; cold-wall heat of ablation; effective heat of ablation; heat of ablation; thermochemical heat of ablation

REFERENCES

- (1) McVey, D. F., Auerbach, I., and McBride, D. D., "Some Observations on the Influence of Graphite Microstructure on Ablation Performance," AIAA Paper 70-155, January 1970.
- (2) Kratsch, K. M., et al., "Graphite Ablation in High Pressure Environments," AIAA Paper No. 68-1153, AIAA Entry Vehicle Systems and Technology Meeting, Williamsburg, VA, Dec. 3-5, 1968.
- (3) Maahs, H. G., Schryer, D. R., "Particle Removal in the Ablation of Artificial Graphite," *AIAA Journal*, Vol 7, No. 11, 1969, pp. 2178-2179.
- (4) AVCO Systems Division, "Thermomechanical Erosion of Ablative Plastic Composites," Quarterly Progress Report No. AVSD-0095-70-CR.
- (5) Hiester, N. K., and Clark, C. F., "Comparative Evaluation of Ablating Materials in Arc Plasma Jets," NASA CR-1207, Stanford Research Institute, Menlo Park, CA, December 1968.
- (6) Ziemke, M. C., "Heat Flux Transducers," *Instruments and Control Systems*, December 1967, pp. 85-88.
- (7) Fay, J. A., and Riddell, F. R., "Theory of Stagnation Point Heat Transfer in Dissociated Air," *Journal of Aeronautical Sciences*, Vol 25, No. 2, February 1958, p. 73.
- (8) Massier, P. F., Back, L. H., and Roschke, E. J., "Comparison of Enthalpy Measurements Obtained in an Internal-High Temperature Flow of Argon as Determined by Conservation of Energy, a Calorimetric Probe, a Flowmeter, and Spectroscopy," JPL SPS 37-45, Vol IV, pp. 141-151.
- (9) Winovich, W., "On the Equilibrium Sonic-Flow Method for Evaluating Electric-Arc Air Heater Performance," NASA TN D-2132
- (10) Anderson, L. A., and Sheldahl, R. E., "Flow-Swallowing Enthalpy Probes in Low Density Plasma Streams," AIAA Paper No. 68-390, AIAA Third Aerodynamic Testing Conference, April 8-10, 1968.
- (11) Pope, R. B., "Measurements of Enthalpy in Low Density Arc-Heated Flows," *AIAA Journal*, Vol 6, No. 1, January 1968, pp. 103-110
- (12) Schmidt, D. L., and Schwartz, H., "Evaluation Methods for Ablative Plastics," *SPE Transactions*, October 1968, pp. 238-250
- (13) John, R., et al., "Arc Heater Characterization of Ablative Plastics," ML-TDR-62-191, October 1964.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).