



Designation: F 1110 – 90 (Reapproved 1998)

## Standard Test Method for Sandwich Corrosion Test<sup>1</sup>

This standard is issued under the fixed designation F 1110; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method defines the procedure for evaluating the corrosivity of materials on aluminum alloys commonly used for aircraft structures. This test method is intended to be used in the qualification and approval of compounds employed in aircraft maintenance operations.

1.2 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements appear in Section 9.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1193 Specification for Reagent Water<sup>2</sup>

D 1748 Test Method for Rust Protection by Metal Preservatives in the Humidity Cabinet<sup>3</sup>

G 46 Guide for Examination and Evaluation of Pitting Corrosion<sup>4</sup>

#### 2.2 Federal Specifications:

QQ-A-250/4 Al Alloy 2024 Plate and Sheet<sup>4</sup>

QQ-A-250/5 Al Alloy Alclad 2024 Plate and Sheet<sup>4</sup>

QQ-A-250/12 Al Alloy 7075 Plate and Sheet<sup>4</sup>

QQ-A-250/13 Al Alloy Alclad 7075 Plate and Sheet<sup>4</sup>

#### 2.3 Military Specification:

MIL-A-8625 Anodic Coatings for Aluminum and Al Alloys<sup>4,5</sup>

### 3. Terminology

#### 3.1 Definition of Term Specific to This Standard:

3.1.1 *sandwich corrosion test*—a comparative accelerated environmental test of the corrosivity of liquid or solid materials on structural aluminum alloys commonly used in aerospace construction.

### 4. Summary of Test Method

4.1 Aluminum coupons having clad or anodized nonclad surfaces are sandwiched together with a filter paper saturated with the test material between the coupons. The sandwiched coupons are cycled between warm ambient air and warm humid air for 7 days. The coupons are then inspected to determine whether corrosion more severe than that caused by reagent water has occurred on the surfaces exposed to the test material. This test method may be used for solutions of dry granular material or for liquid materials.

### 5. Significance and Use

5.1 The data generated by this test method shall be used to determine whether aircraft structural aluminum alloys are liable to be corroded or damaged by application of the test material during routine maintenance operations.

5.2 Interpretation of the sandwich corrosion test results is based on a comparison of the appearance of faying surfaces of three sets of coupons. One set of test coupons is exposed with reagent water only in the faying surfaces, to establish the baseline (controls) against which the panels exposed to the test material are compared. Corrosion at cut edges of the test coupons should be disregarded.

5.3 The relative corrosion severity rating system is provided in order to allow a numerical classification of the test results and to eliminate the necessity for elaborate weight loss measurements. Pitting corrosion, which is rated 4—extensive (severe) corrosion, may involve only a negligible weight loss.

#### 5.4 Relative corrosion severity rating system

0—No visible corrosion

1—Very slight corrosion or discoloration

2—Slight corrosion

3—Moderate corrosion

4—Extensive corrosion or pitting

0—No corrosion

1—Up to 5 % of the surface area corroded

2—5 to 10 %

3—10 to 25 %

4—25 % or more

### 6. Interferences

6.1 Tap water containing large amounts of dissolved solids, especially chlorides, may cause relative severe corrosion of the aluminum control panels. For this reason a reagent water is specified. For comparative purposes, a set of aluminum test panels, with the locally available tap water applied to the filter

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F-7 on Aerospace and Aircraft and is the direct responsibility of Subcommittee F07.07 on Qualification Testing of Aircraft Cleaning Materials.

Current edition approved Jan. 26, 1990. Published March 1990. Originally published as F 1110 – 86. Last previous edition F 1110 – 86. <sup>$\epsilon$ 1</sup>

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 11.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 05.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 03.02.

<sup>5</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

paper, may be run along with the reagent water panels.

6.2 Under certain conditions cellulose filter paper may react with the test aluminum alloy and change the test results. Filter paper made from glass fibers is available, and should be used, except for fluoride-containing compounds.

## 7. Apparatus

7.1 *Humidity Test Cabinet*, as specified in Test Method D 1748 or equal, capable of from 95 to 100 % relative humidity at  $37.7 \pm 1^\circ\text{C}$  ( $100 \pm 2^\circ\text{F}$ ).

7.2 *Oven*, forced air circulation, capable of maintaining  $37.7 \pm 1^\circ\text{C}$  ( $100 \pm 2^\circ\text{F}$ ).

7.3 *Microscope*, binocular, 10× to 40×.

## 8. Reagents and Materials

8.1 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Specification D 1193, Type IV.

8.2 *Aluminum Alloy Coupons*:

8.2.1 Aluminum alloy coupons shall conform to the following Federal Specifications:

QQ-A-250/4, 2024-T3 nonclad

QQ-A-250/5, 2024-T3 Alclad

QQ-A-250/12, 7075-T6 nonclad

QQ-A-250/13, 7075-T6 Alclad

8.2.2 *Coupon Size*—The recommended coupon size 50 by 100 by 1.0 to 1.5 mm (2 by 4 by 0.04 to 0.06 in.) has been found to provide suitable results for comparative tests. Smaller sizes are not recommended, because of the increased variations due to edge effects. Larger coupons are acceptable, but the space requirements for testing and storage should be considered.

8.3 Anodize the nonclad coupons in accordance with Military Specification MIL-A-8625C, Type 1 (Chromic Acid).

8.4 *Filter Paper*—Use Whatman GFA or equal filter paper made from glass fibers, 11 or 13 cms. Filter paper will not be required when the material being tested is a solid. Cellulose filter paper should be used with products containing fluorides.

## 9. Hazards

9.1 The materials used for aircraft maintenance may contain flammable solvents, strong acids or alkalis, or other toxic compounds. Take suitable precautions to prevent personal injury from these hazards. When the composition of the test material is not known, consult the manufacturer to determine whether any hazards exist.

9.2 Exercise special care in handling the chromic acid solution, specified in 8.3 for its etching properties.

## 10. Sampling

10.1 Agitate or thoroughly mix the test material to assure uniformity. Where dilution of the material is required, use reagent water or the solvent specified by the product manufacturer. Apply sufficient test material to saturate the area between the metal coupons.

## 11. Test Specimen

11.1 Prepare three sets of test panels. A test panel set shall consist of eight individual test coupons, sandwiched together in

pairs of coupons of the same alloy and the same surface treatment, to provide four test coupon sandwiches for each test condition. Identify each coupon by impression stamping or other suitable permanent method.

11.2 Clean the panels by solvent wiping, or vapor degreasing. Do not use acid or caustic cleaners. Remove ink stamped markings from the panels. Do not use abrasive materials to clean the panels.

11.3 Prepare the test panel sets as follows for each alloy:

11.3.1 One set for the compound to be tested at use dilution,

11.3.2 One set for the compound to be tested in concentrated form and

11.3.3 One set for controls using reagent water.

## 12. Preparation of Apparatus

12.1 Verify that the humidity cabinet is operating at the specified temperature and humidity.

12.2 Verify that the air oven is operating at the specified temperature, with air circulation.

## 13. Calibration and Standardization

13.1 Since the test coupons include controls for comparative purposes, no special calibration or standardization procedures are required.

## 14. Conditioning

14.1 Conditioning of the test materials or the sets of prepared test coupons is not required. Thoroughly agitate the test sample before application to the test coupons.

14.2 Allow the anodized panels to age for a period of at least 48 h prior to exposure.

## 15. Procedure

15.1 Assemble the cleaned panels into three identical groups each having four different sets of panels suitably identified by permanent marking. Each panel set shall consist of two individual coupons of the same alloy and the same surface treatment.

15.2 Cut a piece of glass fiber filter paper to approximate 25 by 75 mm (1 by 3 in.). Fit this piece over one of the coupons. Add the test solution at the use concentration to the paper until saturated. Cover the wet paper with the second coupon of the sandwich pair. Repeat the operation for each of the coupon sets in the group. This test may be omitted if the test material is to be used in the concentrated form only. See 8.4 for deletion of the filter paper.

15.3 Prepare a second group of panels as outlined in 15.2 except apply the material to be treated in the concentrated as-received condition, without dilution by water or solvents. (Not applicable to dry granular materials.)

15.4 Prepare a third group of panels, as outlined in 15.2, except apply reagent water only to the filter paper between the panels.

15.5 During each test day, expose the panels in the air oven for 8 h followed immediately by exposure in the humidity cabinet. The alternating exposure periods should be started on a Monday morning with the initial exposure in the air oven. Over the following weekend the coupons should be left in the humidity cabinet. Maintain the humidity cabinet at  $37.7 \pm 1^\circ\text{C}$



(100 ± 2°F) and 95 to 100 % relative humidity. Maintain the air oven at 37.7 ± 2.8°C (100 ± 5°F). Expose each set of panels individually, not stacked, in a horizontal position. After exposure, rinse the panels in warm tap water, and scrub lightly with a soft nonmetallic bristle brush. After drying, examine each panel under 10× magnification, and rate each set according to the scales in 5.4.

**16. Interpretation of Results**

16.1 Compare the corrosion rating on the set of panels from the first and second groups with those from the third, Reagent water, control group. Any corrosion in excess of that shown by group 3 shall be cause for rejection. Give pitting corrosion of any panel a severity rating of 4. Disregard any corrosion at the edges of the panel. Compare only those surfaces which were under the filter paper. Pitting is defined in Practice G 46.

**17. Report**

17.1 Prepare a report certifying that the test has been run in accordance with this test method and listing the exact conditions of the test as performed. Tabulate the corrosion rating of all test panels used in the test, and state whether the test compound is considered to be acceptable from a sandwich corrosion standpoint.

**18. Precision and Bias**

18.1 No statement is made about either the precision or bias of this test method since the result merely states whether there is conformance to the criteria for success specified in the accompanying material or process specification of the material being tested, or both.

**APPENDIX**

**(Nonmandatory Information)**

**X1. RECOMMENDED PANEL IDENTIFICATION, TABULATION OF RESULTS, AND EXPOSURE SCHEDULE**

*X1.1 Panel Identification:*

*X1.1.1 Test Material Diluted to Using Concentration:*

- A-1 2024-T3 Nonclad Anodized
- A-2 2024-T3 Alclad
- A-3 7075-T6 Nonclad Anodized
- A-4 7075-T6 Alclad

*X1.1.2 Test Material in Concentrated, As-Received Condition:*

- B-1 2024-T3 Nonclad Anodized
- B-2 2024-T3 Alclad
- B-3 7075-T6 Nonclad Anodized
- B-4 7075-T36 Alclad

*X1.1.3 Specification D 1193, Grade IV Control:*

- C-1 2024-T3 Nonclad Anodized

- C-2 2024-T3 Alclad
- C-3 7075-T6 Nonclad Anodized
- C-4 7075-T6 Alclad

*X1.2 Tabulation of Results:*

X1.2.1 See Fig. X1.1 for a recommended form for tabulation of results.

NOTE 1—Record pitting corrosion separately, if present.

Condition	Alloy			
	1	2	3	4
A—Diluted				
B—Concentrate				
C—Specification D 1193, Type IV				

**FIG. X1.1 Recommended Tabulation of Results**

X1.3 *Exposure Schedule:*

X1.3.1 See Table X1.1 for a recommended exposure schedule.

**TABLE X1.1 Recommended Exposure Schedule<sup>A</sup>**

Step	Exposure Time, <sup>B</sup> h ± ½	Conditions	
		Temperature °C (°F)	Relative Humidity, %
1	8	37.7 (100)	Ambient
2	16	37.7 (100)	95–100
3	8	37.7 (100)	Ambient
4	16	37.7 (100)	95–100
5	8	37.7 (100)	Ambient
6	16	37.7 (100)	95–100
7	8	37.7 (100)	Ambient
8	16	37.7 (100)	95–100
9	8	37.7 (100)	Ambient
10	64	37.7 (100)	95–100

<sup>A</sup>The sequence of steps is optional except tests shall be started on odd numbered steps.

<sup>B</sup>Total testing time is 168 h.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (http://www.astm.org).*