

Designation: F 735 – 94

Standard Test Method for Abrasion Resistance of Transparent Plastics and Coatings Using the Oscillating Sand Method¹

This standard is issued under the fixed designation F 735; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method determines the resistance of transparent plastics and transparent coatings utilized in windows or viewing ports, to surface abrasion using oscillating sand.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates²

D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing³

D 1003 Test Method for Haze and Luminous Transmittance of Transparent Plastics³

E 11 Specification for Wire-Cloth Sieves for Testing Purposes⁴

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method⁴

3. Summary of Test Method

3.1 The test method consists of measuring and recording the haze and light transmission of a test specimen, mounting the specimen so that it forms part of the bottom of a tray (sand cradle), covering the specimen with abrading media, and subjecting the cradle to a specific number of to-and-fro motions. After exposure to the abrasion, the haze and light transmission are remeasured to determine any change in these values.

3.2 At the stroke velocity specified in this practice, the entire mass of sand shifts significantly within the sand cradle because of its inertia; therefore the relative motion between sand and specimen at the interface is large.

¹ This test method is under the jurisdiction of ASTM Committee F-7 on Aerospace and Aircraft and is the direct responsibility of Subcommittee F07.08 in Transparent Enclosures and Materials.

Current edition approved May 15, 1994. Published July 1994. Originally published as F 835 – 81. Last previous edition F 735 – 81(1987) ^{ϵ 1}.

² *Annual Book of ASTM Standards*, Vol 04.02.

³ *Annual Book of ASTM Standards*, Vol 08.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

3.3 The thickness or height of the sand, which rests on top of the test specimen, remains relatively constant over the test specimen itself during the motion of the cradle. Therefore, the average pressure of the sand also remains constant, giving highly reproducible results over the entire surface of the test specimen.

3.4 The degree of abrasion is measured by the amount of change in luminous transmission and haze after exposure to the test.

4. Significance and Use

4.1 Many types of plastics are used in the making of transparencies and enclosures or covers. It is the intent of this test to provide a means of determining the relative abrasion resistance of plastics or coatings, or both, to such operational uses as the cleaning of dirt, removal of bug residue, or any other rubbing action that can cause abrasion.

5. Apparatus

5.1 *Abrader*—The abrader illustrated in Fig. 1 consists of a specimen holder, sand cradle, drive mechanism, variable power supply and counter.

5.1.1 The specimen holder shall have a cutout approximately 100 by 100 mm (4 by 4 in.) to receive the specimen. The specimen shall be mounted flush to within 1 mm (0.04 in.) high with the specimen holder.

5.1.2 The specimen holder forms the bottom of the sand cradle.

TABLE 1 Properties

E11 Sieve Designation		Mean % on Sieve	Standard Deviation, %	Cululative % Retained, Mean
U.S. No	mm			
8	2.36	30.0	7.4	30.0
10	2.00	40.0	8.4	70.0
12	1.70	22.0	7.8	92.0
14	1.40	6.0	1.1	98.0
Pan	...	2.0	0.7	100.0

^A Effective size at 90 % retained = 1.70 \pm 0.10 mm. Uniformity Coefficient = 1.29 \pm 0.05 mm Shape Factor = 0.40 \pm 0.07 mm.

5.1.3 The cradle size, as defined in Fig. 1 will provide a 13-mm (0.50-in.) head of sand, utilizing 1000 g (2.2 lb).

5.1.4 A drive mechanism shall provide 300 strokes per minute of reciprocating motion of approximately 100-mm (4-in.) travel. Motion in one direction is defined as one stroke.

5.1.5 A variable power supply shall be utilized to control the abrader motor to operate at 300 strokes per minute.

5.1.6 A counter shall record the number of strokes during a test.

5.2 *Photometer*—An integrating sphere photoelectric photometer, described in Test Method D 1003, shall be used to measure the light scattered by the abraded surface.

6. Reagents and Materials

6.1 *Abrading Medium—Quartz Sand*⁵—The sand shall be quartz silica grid sized 6/14 and shall meet the following requirements:

6.1.1 *Properties*—See Table 1.

6.1.2 *Test Methods*:

NOTE 1—These tests need be applied only when qualifying a new supply of sand.

6.1.2.1 Perform sieve analysis in accordance with Method C 136.

⁵ Satisfactory sand (Texsan Filter Sand #7) has been procured from Vulcan Materials Company, White Mines Division, Industrial Sand Products. 1-(800)-537-6371.

FIG. 1 Oscillating Sand Abrader

6.1.2.2 Plot the cumulative percent retained, on logarithmic probability paper.

6.1.2.3 Read from the plot the sizes in millimetres at 40, 50, and 90 % retained.

6.1.2.4 Calculate the uniformity coefficient as the ratio (millimetres at 40 %/millimetres at 90 %).

6.1.2.5 Count out 100 grains, taking care to be nonselective, and weigh to ± 10 mg.

6.1.2.6 Calculate the shape factor as

$$\frac{(\text{weight of 100 particles})}{265 (\text{millimetres at 50 \% retained})^3} \quad (1)$$

NOTE 2—There are many conflicting definitions of shape factor.⁶ The definition given in 6.1.2.6 is arbitrary and not comparable with any others, except that for a single quartz sphere it has the usual value of 0.524 ($\pi/6$).

7. Test Specimens

7.1 The specimens shall be clean, transparent plates, 100-mm (4-in.) square, having both sides substantially plane

⁶ Orr, C., and Dallavalle, J. M., *Fine Particle Measurement*, The Macmillan Co., New York, NY 1959, pp 35–36.

F 735

and parallel. Three specimens shall be tested. Any specimen thickness can be utilized when positioned in the specimen holder to conform to the mounting tolerances.

8. Conditioning

8.1 Where conditioning of the test specimen is required, utilize Procedure A of Practice D 618.

8.2 Tests shall be conducted in the Standard Laboratory Atmosphere of $23 \pm 2^\circ\text{C}$ and $50 \pm 5\%$ relative humidity, unless otherwise specified.

9. Procedure

9.1 Calibrate motor speed to 300 strokes per minute with the specimen in the specimen holder plate and the desired quantity of sand in the cradle. Sand used for calibration shall be discarded.

9.2 Measure transmission and haze prior to testing specimen in accordance with 3.3.

9.3 Mount specimen in holding plate, using protective means to prevent abrasion or scratching of bottom surface of specimen.

9.4 Cover specimen with sand to a uniform depth of 13 mm (0.50 in.).

9.4.1 A given batch of sand may be used for a maximum of 600 strokes. New sand shall be used for each specimen tested.

9.5 Subject the specimen to 100, 200, 300, and 600 strokes.

9.6 After each increment (as listed in 9.5) of strokes, remove the specimen from the holder. Handle specimen by edges only. Wash with distilled water for a minimum of 10 s by

holding under a stream or by swirling under water in a container. Dry by blowing lightly with filtered air or nitrogen. Measure the transmission and haze in accordance with 9.7.

9.7 Using a photoelectric, integrating sphere photometer and Test Method D 1003, measure the percentage of transmitted light and percent of haze.

10. Report

10.1 The report shall include the following:

10.1.1 Type of material being tested,

10.1.2 The percentage of the transmitted light and percent haze for each specimen tested, both before and after exposure to abrasion of 100, 200, 300, and 600 strokes, and

10.1.3 Test results shall be reported as the average of the three specimens tested.

11. Precision and Bias

11.1 *Precision*—A round robin has been completed. However, only five (5) laboratories, rather than six (6) per Practice E 691 were used, because no others were found to exist. Data is currently under evaluation and a precision statement will be formulated.

11.2 *Bias*—No justifiable statement can be made on the bias of the procedure in Test Method F 735 for measuring abrasion, because there is no standard material.

12. Keywords

12.1 abrasion; haze; plastic; transmission; transparent; strokes

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).