



Designation: D 2943 – 96 (Reapproved 2000)

## Standard Test Method for Aluminum Scratch of 1,1,1-Trichloroethane to Determine Stability<sup>1</sup>

This standard is issued under the fixed designation D 2943; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This is a screening test method to determine if sufficient inhibitors are present in 1,1,1-trichloroethane to provide at least minimal stability in the presence of aluminum.

1.2 Solvent passing this test method may not be stable for all applications.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* A specific hazard statement is given in Section 6.

### 2. Summary of Test Method

2.1 A cleaned, degreased, dry metal coupon of aluminum alloy is immersed in inhibited 1,1,1-trichloroethane and scratched while in the solvent. After sufficient time has elapsed to allow any reaction to occur, the presence or absence of bubbling, solvent discoloration, or dark resinous material is noted. The 1,1,1-trichloroethane is sufficiently inhibited only if none of these conditions is observed.

### 3. Significance and Use

3.1 The degradation of insufficiently stabilized 1,1,1-trichloroethane, in the presence of aluminum, results in the formation of hydrochloric acid and polymeric residue. Thus, if such degradation is allowed to continue, the aluminum will be corroded and the 1,1,1-trichloroethane rendered unusable. The presence of free water invalidates this test method.

3.2 This test method can be used to determine if 1,1,1-trichloroethane is sufficiently stabilized to inhibit reaction with aluminum or aluminum alloys. Solvent passing this test method still may not be stable for all applications. Consult a producer for use applications.

3.3 Aluminum should not be used as a material of construction for pumps, tanks, pipelines, valves, spray equipment, or other handling equipment used for chlorinated solvents. Prop-

erly stabilized halogenated solvents are, however, commonly used in cleaning aluminum and other sensitive metals.

### 4. Apparatus

4.1 *Aluminum Sheet Metal*, designated ASTM Alloy 1100 (UNS No. A91100),<sup>2</sup> 0.016 to 0.040 in. thick.

4.2 *Mild Steel Metal Object*, such as an ice pick sharpened to lead pencil-sized point.

### 5. Preparation of Aluminum Coupon

5.1 Degrease an aluminum coupon, 1 by 1 in., by rinsing in a commercial grade of inhibited 1,1,1-trichloroethane. Hand-sand both sides of the aluminum coupon lightly with a fine emery cloth, and rinse the coupon again. The surface should be bright and free of haze.

### 6. Hazards

6.1 This test method should be performed in a fume hood. Insufficiently inhibited solvent can react with aluminum to form hydrogen and hydrogen chloride gases. Solvent vapors are also present. Their release to the atmosphere must be minimized.

### 7. Procedure

7.1 Conduct this test method at room temperature. Measure 50 mL of inhibited 1,1,1-trichloroethane into a clean solvent-rinsed glass beaker. Place a freshly prepared aluminum coupon in the solvent sample in a horizontal position on the bottom of the beaker. Scratch (Note 1) the top surface of the submerged aluminum coupon with a sharply pointed mild steel instrument. Make three scratches approximately equally spaced and 0.005 in. deep in one direction. Then make three additional scratches at right angles to the original three (Note 2). Observe the aluminum coupon after 10 min and again after 1 h has elapsed. In the event that continued decomposition occurs after 1 h, add water to stop the reaction, remove the aluminum coupon, and discard the solvent in a solvent container to prevent evaporation.

NOTE 1—The scratch should be a lateral scrape rather than a vertical perforation.


<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D26 on Halogenated Organic Solvents and Fire Extinguishing Agents and is the direct responsibility of Subcommittee D26.04 on Test Methods.

Current edition approved June 10, 1996. Published August 1996. Originally published as D 2943 – 71 T. Last previous edition D 2943 – 92.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 02.02.



NOTE 2—Scratches are to appear as follows:



## 8. Report

8.1 For each test method, report observations as follows:

8.1.1 Passes/no reaction.

8.1.2 Fails/the appearance of gas bubbles, color formation, or metal corrosion at the edge of the scratch marks are evidence

of failure to pass the test method.

8.2 The solvent should be considered sufficiently stabilized for many uses in the presence of aluminum or aluminum alloys only if no reaction occurs. The absence of reactivity in this test method may not indicate stability for all applications.

## 9. Precision and Bias

9.1 Only visual observations are reported. No precision and bias statements can be made.

## 10. Keywords

10.1 aluminum; aluminum scratch test; inhibitors; stability test; 1,1,1-trichloroethane

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*