



## Standard Specification for Reclaimed 1,1,2-Trichloro 1,2,2-Trifluoroethane<sup>1</sup>

This standard is issued under the fixed designation D 5248; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers the three grades of 1,1,2-trichloro 1,2,2-trifluoroethane<sup>2</sup> typically needed in various industries. It may be used as a reference document by purchasers or by persons establishing in-house, 1,1,2-trichloro 1,2,2-trifluoroethane recovery programs.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 1064 Test Methods for Iron in Rosin Tall Oil Fatty Acids and Other Related Products<sup>3</sup>
- D 2108 Test Method for Color of Halogenated Organic Solvents and Their Admixtures (Platinum-Cobalt Scale)<sup>4</sup>
- D 2109 Test Methods for Nonvolatile Matter in Halogenated Organic Solvents and Their Admixtures<sup>4</sup>
- D 2111 Test Methods for Specific Gravity of Halogenated Organic Solvents and Their Admixtures<sup>4</sup>
- D 3401 Test Methods for Water in Halogenated Organic Solvents and Their Admixtures<sup>4</sup>
- D 3443 Test Method for Chloride in Trichlorotrifluoroethane<sup>4</sup>
- D 3444 Test Method for Total Acid Number of Trichlorotrifluoroethane<sup>4</sup>
- D 3447 Test Method for Halogenated Organic Solvents<sup>4</sup>
- D 3741 Test Method for Appearance of Admixtures Containing Halogenated Organic Solvents<sup>4</sup>

### 3. Classification

- 3.1 *Type I*—Generally recognized for use in precision applications.
- 3.2 *Type II*—Use for less demanding precision applications.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-26 on Halogenated Organic Solvents and Fire Extinguishing Agents and is the direct responsibility of Subcommittee D26.08 on Recovered Solvents Specifications.

Current edition approved Dec. 10, 1996. Published June 1997. Originally published as D 5248 – 92. Last previous edition D 5248 – 92 (1996).

<sup>2</sup> 1,1,2-trichloro 1,2,2-trifluoroethane: CAS No. 76-13-1.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 06.03.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 15.05.

TABLE 1 Physical Properties Type I

Property	Specification	Test Method
Specific Gravity, 20/20	1.54 to 1.57	D 2111
Chloride, ppm, max	0.1	D 3443
Acid number	0.003	D 3444
Non-volatile residue, ppm, max	10	D 2109
Water, ppm, max	25	D 3401 or D1064
1,1,2-trichloro 1,2,2-trifluoroethane content, wt %, min	99.5	D 3447
1,1,1-trichloroethane content, wt %, max	0.02	D 3447
Color, Pt-Co, max	10	D 2108
Appearance	clear and free from suspended matter	D 3741

3.3 *Type III*—General-purpose technical grade.

### 4. Properties

- 4.1 Reclaimed 1,1,2-trichloro 1,2,2-trifluoroethane Type I shall meet the requirements prescribed in Table 1.
- 4.2 Reclaimed 1,1,2-trichloro 1,2,2-trifluoroethane Type II shall meet the requirements prescribed in Table 2.
- 4.3 Reclaimed 1,1,2-trichloro 1,2,2-trifluoroethane Type III shall meet the requirements prescribed in Table 3 .

### 5. Keywords

- 5.1 1,1,2-trichloro 1,2,2-trifluoroethane; CFC 113; Type I; Type II; Type III

**TABLE 2 Physical Properties Type II**

Property	Specification	Test Method
Specific Gravity, 20/20	1.53 to 1.57	D 2111
Chloride, ppm, max	0.2	D 3443
Acid number	not tested	D 3444
Non-volatile residue, ppm, max	20	D 2109
Water, ppm, max	50	D 3401 or D1064
1,1,2-trichloro 1,2,2-trifluoroethane content, wt %, min	99.0	D 3447
1,1,1-trichloroethane content, wt %, max	0.05	D 3447
Color, Pt-Co, max	10	D 2108
Appearance	clear and free from suspended matter	D 3741

**TABLE 3 Physical Properties Type III**

Property	Specification	Test Method
Specific Gravity, 20/20	1.52 to 1.57	D 2111
Chloride, ppm, max	0.2	D 3443
Acid number	not tested	D 3444
Non-volatile residue, ppm, max	25	D 2109
Water, ppm, max	100	D 3401 or D1064
1,1,2-trichloro 1,2,2-trifluoroethane content, wt %, min	98.0	D 3447
1,1,1-trichloroethane content, wt %, max	0.1	D 3447
Color, Pt-Co, max	25	D 2108
Appearance	clear and free from suspended matter	D 3741

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*