



Standard Test Method for Torque-Tension Relationship of Adhesives Used on Threaded Fasteners (Lubricity)¹

This standard is issued under the fixed designation D 5648; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method covers the determination of the torque-tension relationship (lubricity) of adhesives used for locking and sealing threaded fasteners.

1.2 The values stated in inch-pounds are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

D 907 Terminology of Adhesives²

2.2 *Society of Automotive Engineers Standards:*

SAE J174 Torque Tension Test Procedure for Steel Threaded Fasteners³

SAE J429 Mechanical and Material Requirements for Externally Threaded Fasteners³

2.3 *Federal Specification:*

FF-N-836 Nut: Square, Hexagon, Cap, Slotted, Castle, Knurled, Welding and Single Ball Seat⁴

3. Terminology

3.1 *Definitions*—Many of the terms in this test method are defined in Terminology D 907.

4. Summary of Test Method

4.1 This test method consists of applying adhesive to a threaded fastener and measuring the developed tension applied to the fastener at specified torques. Alternatively, the torque required to reach specified levels of bolt tension may be measured.

¹ This test method is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.80 on Metal Bonding Adhesives.

Current edition approved March 10, 2001. Published May 2001. Originally published as D 5648 - 94. Last previous edition D 5648 - 94.

² *Annual Book of ASTM Standards*, Vol 15.06.

³ Available from the Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096.

⁴ Available from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20403.

5. Significance and Use

5.1 On some applications of threaded fasteners, it is desirable to control either the amount of developed tension when a specified range of torque has been applied or the torque required to develop a specified range of tension. This test method is used to determine the effect of using adhesives on the torque-tension relationship of threaded fasteners.

5.2 Accurate torque-tension relationships may be measured only by defining and controlling the many related test parameters.

6. Apparatus

6.1 *Tension-Measuring Device*, capable of measuring the axial tension induced in the bolt as it is tightened, having an accuracy within $\pm 5\%$ of the test load.

6.2 *Torque-Measuring Device*, of suitable capacity having an accuracy within $\pm 5\%$ of a given torque reading.

7. Test Specimens

7.1 *Bolts*—As-received, phosphate-and-oil-treated, $\frac{3}{8}$ -in. size, 16 threads per inch, Unified National Coarse thread series ($\frac{3}{8}$ by 16 UNC), Grade 5 bolts in accordance with SAE J429, having a minimum length of 1½ in. (38.1 mm) with hexagonal head.

7.2 *Steel Nuts*—As-received, Type II, Style 4, nominally $\frac{21}{64}$ in. (8.3 mm) thick, conforming to Fed. Spec. FF-N-836.

NOTE 1—Other fastener sizes and substrates may be used upon agreement between the supplier and the user of adhesives.

7.3 *Hardened Washers*, conforming to the dimensional, metallurgical, mechanical, and finish requirements given in Table Number 1 of SAE J174.

8. Procedure

8.1 Determine the torque-tension relationship on not less than five specimens as follows:

8.1.1 For liquid adhesives, insert the bolt in the tension-measuring device and apply the adhesive to the exposed threads of the bolt. Also apply the adhesive to the threads of the nut.

8.1.2 Place a new hardened washer over the exposed end of the bolt until it squarely contacts the bearing surface of the device.

8.1.3 Assemble the nut onto the bolt by hand until it

contacts the hardened washer.

8.1.4 Using the torque-measuring device, tighten the nut continuously and uniformly at a speed not to exceed 30 r/min, making sure that the washer and the bolt are restrained from turning.

8.1.5 When testing specimens in accordance with 7.1 and 7.2, record bolt tensions, not exceeding 75 % of the proof load, at 10, 20, 30, and 40-ft-lb (13.6, 27.1, 40.7, and 54.2-Nm) torque.

8.1.6 Alternatively, record torque at agreed-upon levels of bolt tension.

NOTE 2—When other fastener sizes are used, appropriate torque and load levels are specified.

9. Report

9.1 Report the following information:

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

9.1.1 Complete identification of the adhesive tested, including type, source, date manufactured, manufacturer's code numbers, and form.

9.1.2 Description of the apparatus used to measure tension and torque.

9.1.3 Number of specimens tested.

9.1.4 Maximum, minimum, and average tension values at each applied torque, or maximum, minimum, and average torque values at each level of bolt tension.

10. Precision and Bias

10.1 Precision and bias for this test method are being determined and will be available by April 2005.

11. Keywords

11.1 adhesive; lubricity; threadlocking; torque tension