



# Standard Test Method for Lap Shear Adhesion for Fiber Reinforced Plastic (FRP) Bonding<sup>1</sup>

This standard is issued under the fixed designation D 5868; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method describes a lap shear test for use in measuring the bonding characteristics of adhesives for joining fiber reinforced plastics to themselves and to metals. The method is applicable to random and fiber oriented FRP.

1.2 This test method is intended to complement Test Method D 1002 and extend the application to single-lap shear adhesive joints of fiber-reinforced plastic (FRP) adherends. This test method is useful for generating comparative apparent shear strength data for joints made from a number of FRP materials, providing a means by which FRP surface treatments may be compared.

1.3 The values stated in inch-pound units are to be regarded as the standard. The SI values in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

D 1002 Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading (Metal-to-Metal)<sup>2</sup>

D 2093 Practice for Preparation of Surfaces of Plastics Prior to Adhesive Bonding<sup>2</sup>

D 3163 Test Method for Determining the Strength of Adhesively Bonded Rigid Plastic Lap-Shear Joints in Shear by Tension Loading<sup>2</sup>

D 4896 Guide for Use of Adhesive-Bonded Single Lap-Joint Specimen Test Results<sup>2</sup>

D 907 Terminology of Adhesives<sup>2</sup>

D 5573 Practice for Classifying Failure Modes in Fiber-Reinforced-Plastic (FRP) Joints<sup>2</sup>

E 4 Practices for Force Verification of Testing Machines<sup>3</sup>

### 2.2 SAE Standard:

SAE J1525 Lap Shear Test for Automotive-Type Adhesives

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-14 and is the direct responsibility of Subcommittee D14.40 on Adhesives for Plastics.

Current edition approved Dec. 10, 1995. Published February 1996.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 15.06.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 03.01.

for Fiber Reinforced Plastic (FRP) Bonding<sup>4</sup>

## 3. Terminology

3.1 Adhesive terminology for this test method is covered in Terminology D 907.

## 4. Summary of Test Method

4.1 This test method describes a procedure for the testing of lap shear bond strengths, using composite materials not recommended in Test Method D 3163 such as FRP.

## 5. Significance and Use

5.1 Due to the increased use of adhesively-bonded FRP as a result of the inherent advantages afforded by bonded rather than mechanically-fastened joints (particularly the alleviation of stress risers and stress cracking), there is a need for tests by which joints of various FRP substrates and adhesives may be compared. This test method is intended to meet such a need.

5.2 Additional information on significance and use may be found in Guide D 4896.

## 6. Interference

6.1 Apparent shear strength may be affected by substrate properties, such as moisture absorption and strength.

## 7. Apparatus

7.1 *Testing Machine*, conforming to the requirements and having the capabilities of the machine in Practices E 4. Likewise, the grips should be capable of securely grasping the specimen throughout the test without allowing the specimen to slip. The grips should also be self-aligning.

## 8. Procedure

### 8.1 Test Substrate:

8.1.1 *Substrates*—Fiber reinforced plastic (FRP) as specified, with metal composition (heat treat, temper, and condition) and roughness as specified when bonding FRP to metal.

8.1.2 *Dimensions*—Fiber-reinforced plastic parts shall be cut into flat coupons 1 by 4 in. (25.4 by 100 mm) at a nominal thickness of 0.1 in. (2.5 mm). In the case of FRP-to-metal bonding, metal thickness will be nominally 0.06 in. (1.5 mm).

<sup>4</sup> Available from the Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

It is recommended that a diamond tip water-cooled saw blade be used, or a cutting method capable of producing sharp cut edges.

8.2 *Surface Preparations:*

8.2.1 Prepare the surface of the FRP in accordance with Practice D 2093, or as recommended by the adhesive manufacturer. Surface roughening, solvent cleaning, and surface primers are acceptable, provided they do not reduce the FRP bulk properties. The surface preparation used shall be adaptable to actual production conditions.

8.2.2 Prepare the surfaces of metals to eliminate burrs or bevels. Clean and dry them or surface treat them prior to bonding by using procedures prescribed by the adhesive manufacturer.

8.3 *Preparation of Test Joints:*

8.3.1 *Applications of Adhesive*—The adhesive will be applied in accordance with the adhesive supplier’s recommendations or as documented in the test report. In the case of two-part adhesives, mixing will be in accordance with the supplier’s suggested procedures.

8.3.2 *Adhesive Cure*—The adhesive will be cured at room temperature or elevated temperature using prescribed conditions determined by the adhesive supplier.

8.3.3 *Joint Geometry*—Control joint geometry by appropriate fixturing, using glass beads or other suitable means to control a 0.03-in. (0.76-mm) adhesive bondline thickness. The amount of glass beads in the glue line will be the minimum number needed to hold bondline thickness. Fixturing pressure will be allowed. Lap shear overlap will be 1 by 1 in. (25.4 by 25.4 mm). (See Fig. 1.)




FIG. 1 Lap Shear Overlay

8.3.4 *Conditioning*—Allow bonded parts to cool to room temperature for at least 1 h if elevated temperature cures are employed. If the adhesive is room-temperature cured, allow full-cure time plus 10 % prior to testing.

8.4 *Testing:*

8.4.1 The testing machine shall conform to the requirements and have the capabilities of the machine in Practices E 4. It shall have a suitable pair of grips to hold test samples without allowing slip. Initial grip separation shall be 3 in. (75 mm) with 1 in. (25.4 mm) minimum of each sample end held in the test grips.

8.4.2 The specimen loading rate is 0.5 in. (13 mm)/min. Note that a loading rate of 0.5 is an important difference compared to other ASTM standards.

8.4.3 Prepare a minimum of five lap shear samples in each case and test.

9. Report

9.1 Report the following information:

9.1.1 Complete identification of the adhesive tested, including type and manufacturer’s code number.

9.1.2 Complete identification of the substrates used (including type of resin and fiber orientation) and method of surface preparation prior to bonding.

9.1.3 Cure schedule time and temperature for bonding sample, as well as any other conditions, such as sample conditioning, environmental exposures, etc.

9.1.4 Individual peak load values, psi (kPa) and averages by maximum and minimum values.

9.1.5 Test temperature and conditions.

9.1.6 Type of failure (such as fiber tear, cohesive, adhesive) should be reported, in accordance with Practice D 5573.

10. Precision and Bias

10.1 Precision and bias for this test method have not been determined, since resources necessary to do round-robin testing have not been forthcoming.

11. Keywords

11.1 composite; FRP; lap shear

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (http://www.astm.org).*