



Designation: D 899 – 9400

Standard Test Method Practice for Applied Weight Per Unit Area of Liquid Adhesive¹

This standard is issued under the fixed designation D 899; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 ~~This test method covers practice~~ provides a procedure for the ~~determination~~ estimation of the quantity of liquid adhesive applied in a spreading or coating operation.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

¹ ~~This test method practice~~ is under the jurisdiction of ASTM Committee D-14 on Adhesives and is the direct responsibility of Subcommittee D14.10 on Working Properties.

Current edition approved ~~Dec. 15, 1994~~ May 10, 2000. Published ~~February 1995~~ August 2000. Originally published as D 899 – 47 T. Last previous edition D 899 – 894.

3. Terminology

3.1 *Definitions*—Several terms in this ~~test method~~ practice are defined in accordance with Terminology D 907.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *spreading or coating weight per unit area, n*—the total quantity of liquid adhesive uniformly applied, expressed in pounds per thousand square feet of joint or surface area. (See *spread* in Terminology D 907.)

3.2.2 *test specimen, n*—the material that is to be coated with adhesive. (See *adherend* in Terminology D 907).

3.2.3 *total quantity of liquid adhesive applied*— the weight of the adhesive on the test specimen as applied on the surface or at the glue joint, whether resulting from a single spread, a double spread, or multiple applications.

4. Significance and Use

~~4.1 This test method offers a quantitative measure~~

4.1 For the bonding of adherends, the amount of adhesive applied present is critical and it is important to a substrate. It helps understand that this practice does not ensure sufficient adhesive is present on the adherend surface.

4.2 This practice can be used to supplement industry uses such as that of visually checking the proper amount spread or the use of mil-thickness gages.

4.3 In laboratory and industrial operations, hand or mechanical application of adhesives can be duplicated for an optimum glue line. cost savings using this practice.

5. Apparatus

5.1 The following apparatus is required for this ~~test method~~ practice:

5.1.1 A *balance*, capable of weighing the material accurately to the nearest 1 %, and

5.1.2 A *suitable instrument* for measuring the linear dimensions of the specimens to the nearest 1 %.

6. Test Specimens

6.1 Select test specimens from portions of the actual material to be coated or spread, or from the same lot or a similar one, having the same physical characteristics such as thickness, density, or texture.

6.2 The size of the specimen may vary with the nature of the substrate.

NOTE 1—Materials of low porosity normally require larger test specimens than materials of high porosity.

6.3 Use simple geometric shapes for the test specimens to facilitate precise measurement of dimensions.

6.4 For operations involving the coating or spreading of sheeted stock, individual plies or lamina of the adherend, a minimum of 5 test specimens is required for determining the average weight of liquid adhesive applied.

6.5 For operations where the test specimen is in continuous form, such as roll stock of paper or fabric, use a test specimen sufficient in size to reflect accurately the average spreading or coating weight of liquid adhesive.

7. Conditioning

7.1 Prior to the application of the adhesive, bring the test specimens to equilibrium with the atmospheric conditions prevailing under actual or contemplated operational use.

8. Procedure

8.1 Determine the linear dimensions of the test specimens and calculate their areas to an accuracy of 1 %. Determine the weight of the test specimens to the nearest 1 %.

8.2 Apply the adhesive to the test specimens in accordance with the procedure recommended by the manufacturer, and reweigh the specimens immediately.

8.3 Use only test specimens reflecting a normal uniform application of adhesive (by visual inspection) in calculating the weight of liquid adhesive applied.

9. Calculation

9.1 Calculate the weight of liquid adhesive applied as follows:

When W_2 and W_1 are expressed in grams:

$$S = [(W_2 - W_1) \times 317.5] / (N \times A) \quad (1)$$

When W_2 and W_1 are expressed in ounces:

² Annual Book of ASTM Standards, Vol 15.06.

$$S = [(W_2 - W_1) \times 9000]/(N \times A) \quad (2)$$

where:

- S = weight of liquid adhesive applied, expressed in pounds per thousand square feet of joint or surface area,
- W_2 = weight of specimen immediately after application of the adhesive,
- W_1 = weight of specimen before applying the adhesive,
- A = area of test specimen in square inches, and
- N = number of surfaces spread.

NOTE 2—For bonding operations where both contacting surfaces of the joint are spread with adhesive, the formulas above should be used for each surface spread and the combined weight shall equal the total weight of adhesive applied.

10. Report

10.1 Report the following information:

- 10.1.1 Complete identification of the adhesive applied,
- 10.1.2 Method of applying adhesive,
- 10.1.3 Complete description of the adherend test specimens (composition or type, moisture content, size, source, etc.)
- 10.1.4 Number of test specimens used (or total area of test specimens if from a continuous operation) and calculated weight of adhesive applied to each specimen,
- 10.1.5 The average calculated weight of the liquid adhesive applied per thousand square feet of surface of joint area, and
- 10.1.6 Any qualifying remarks concerning the test procedure.

11. Precision and Bias

~~11.1 There is no basis for a statement of precision or bias concerning the reproducibility of results among laboratories. The test by its nature, determining the weight of the applied liquid adhesive per unit area, is not one that can yield results which can be verified by round-robin testing. For this test method, the two measurements, weight and area, are fixed by individual circumstances. Interlaboratory testing would serve no useful purpose.~~

12. Keywords

- ~~12.1~~ coating weight; spread weight

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).